LA-UR-20-22761

Approved for public release; distribution is unlimited.

Title: Process Development of a Direct Cast U-6Nb 250 mm Cylinder

Author(s): Aikin, Robert M. Jr.

Intended for: Report

Issued: 2020-04-06

Disclaimer:

Los Alamos National Laboratory, an affirmative action/equal opportunity employer, is operated by Triad National Security, LLC for the National Nuclear Security Administration of U.S. Department of Energy under contract 89233218CNA000001. By approving this article, the publisher recognizes that the U.S. Government retains nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes. Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy. Los Alamos National Laboratory strongly supports academic freedom and a researcher's right to publish; as an institution, however, the Laboratory does not endorse the viewpoint of a publication or guarantee its technical correctness.

Process Development of a Direct Cast U-6Nb 250 mm Cylinder

Robert M. Aikin Jr.

*Foundry & Solidification Science Team
Sigma 1 – Fabrication Manufacturing Science
Los Alamos National Laboratory
P.O. Box 1663, Los Alamos, NM 87544*

April 1, 2020

Abstract

Direct Casting is the process of casting a near-net shape part of U-6wt%Nb in a multi-zone VIM furnace for subsequent heat treatment and machining in to a final component. This interim report describes ongoing work to further develop a sound technical basis and best practices for mold design and process parameters for the Direct Casting of U-6Nb components with a cylindrical geometry. Specifically, process parameters and mold design are examined in detail for producing a hollow cylinder 250 mm diameter by 450 mm long which is 10 to 12 mm thick. The goal is to efficiently produce a sound casting with a minimum of microporosity and uniform niobium composition.

Table of Contents

Abstract	ii
Table of Contents	iii
1. Introduction	1
1.1 <i>Review of Previous Work on Casting U-6Nb Cylinders</i>	1
1.1.1 <i>250 mm Diameter Cylinders – ACTI-Testworks</i>	1
1.1.2 <i>120 mm Diameter Cylinders</i>	2
1.1.3 <i>250 mm Diameter Cylinders – Revisited</i>	2
1.2 <i>Multi-Zone Furnace and Furnace Modifications</i>	3
1.3 <i>Goals and Casting Design Approach</i>	4
1.3.1 <i>Goal</i>	4
1.3.3 <i>Segregation in U-Nb Castings</i>	5
1.3.2 <i>Feeding</i>	6
2. Counter-Gravity No-Funnel 250 mm Cylinder – 10 mm Thick Version A	8
2.1 <i>Casting and Mold Design</i>	8
2.2 <i>Casting 19K-801 – Mold Version A with $T_{top}=900^{\circ}\text{C}$ and $T_{bottom}=1250^{\circ}\text{C}$</i>	10
2.2.1 <i>Casting Setup</i>	10
2.2.2 <i>Casting and Cooling Curves</i>	11
2.2.3 <i>Breakout</i>	13
2.2.4 <i>Analysis</i>	13
2.3 <i>Casting 19K-807 – Mold Version. A with $T_{top}=1000^{\circ}\text{C}$ and $T_{bottom}=1200^{\circ}\text{C}$</i>	14
2.3.1 <i>Casting Setup</i>	14
2.3.2 <i>Casting and Cooling Curves</i>	15
2.3.3 <i>Breakout</i>	17
2.3.4 <i>Analysis</i>	17
3. Top-Fill 250 mm Cylinder – 10 mm Thick	19
3.1 <i>Casting and Mold Design</i>	19
3.2 <i>Casting 19K-829 – Top Fill with $T_{top}=1250^{\circ}\text{C}$ and $T_{bottom}=920^{\circ}\text{C}$</i>	19
3.2.1 <i>Casting Setup</i>	19
3.3.2 <i>Casting and Cooling Curves</i>	20
3.2.3 <i>Breakout</i>	22
3.2.4 <i>Analysis</i>	22
4. Counter-Gravity No-Funnel 250 mm Cylinder – 12 mm Thick Version B	24
4.1 <i>Casting and Mold Design</i>	24
4.1.1 <i>Change in Casting Thickness</i>	24
4.1.2 <i>Runner Redesign</i>	24
4.2 <i>Casting 19K-844 – Mold Version B with $T_{top}=1000^{\circ}\text{C}$ and $T_{bottom}=1250^{\circ}\text{C}$</i>	25
4.2.1 <i>Casting Setup</i>	25
4.2.2 <i>Casting and Cooling Curves</i>	26
4.2.3 <i>Breakout</i>	28
4.2.4 <i>Analysis</i>	28
4.3 <i>Casting 19K-845 – Mold Version B with $T_{top}=1000^{\circ}\text{C}$ and $T_{bottom}=1230^{\circ}\text{C}$</i>	28
4.3.1 <i>Casting Setup</i>	28
4.3.2 <i>Casting and Cooling Curves</i>	29
	iii

4.3.3	<i>Breakout</i>	31
4.3.4	<i>Analysis</i>	31
5.	Discussion	32
5.1	<i>Solidification Time</i>	32
5.2	<i>Microporosity</i>	32
5.3	<i>Filling of the Casting Cavity</i>	33
5.4	<i>Chemical Analysis</i>	33
6.	Conclusions and Design Recommendations	35
7.	Acknowledgement	36
8.	References	36
	TABLES	37
	FIGURES	46
	Appendix A – Counter Gravity No-Funnel 250 mm Cylinder Mold Drawings ver. A (10 mm thick)	138
	Appendix B – Top Pour 250 mm Cylinder Mold Drawings ver. J	148
	Appendix C – Counter Gravity No-Funnel 250 mm Cylinder Mold Drawings ver. B (12 mm thick)	158

1. Introduction

Direct Casting is the process of casting a near-net shape part of U-6wt%Nb in a multi-zone VIM furnace for subsequent heat treatment and machining in to a final component. This interim report describes ongoing work to further develop a sound technical basis and best practices for mold design and process parameters for the Direct Casting of U-6Nb components with a cylindrical geometry. Specifically, process parameters and mold design are examined in detail for producing a 250 mm diameter by 450 mm long cylinder of 10 to 12 mm thick. The goal is to efficiently produce a sound casting with a minimum of microporosity and uniform niobium composition.

Prior work had tried unsuccessfully to cast cylinders of this size using a mold design with separate crucible and mold stack. These castings had unacceptable levels microporosity and niobium segregation, but more importantly most castings resulted in a partially filled mold which did not have the intended geometry [1]. This work will be reviewed in Section 2. In this work, this same part was cast with mold and crucible integrated into a single mold stack.

Throughout this work heavily instrumented castings, with thermocouples in mold and casting cavity, are used to gain greater insight and understand the solidification process occurring during casting. Process variations examined include gating design and mold temperature. Analysis includes analysis of the cooling curves, destructive analysis of the casting (including metallographic examination for microporosity), and chemical analysis for Nb segregation.

1.1 Review of Previous Work on Casting U-6Nb Cylinders

Prior work on casting cylinders at LANL used LANL's 3-zone furnace with an isolated crucible. This configuration, shown in Fig. 1.1, segment's the furnace into an upper hot zone with the crucible and a bottom hot zone with the two mold coils. Between these two zones there was a shelf that supported the crucible and had a 100 mm hole in it. This shelf is comprised of a 3/8 inch thick steel plated supporting a layer of insulating fire brick. This segmentation of the furnace

- a) requires a funnel on top of the mold stack to direct molten metal into the mold (because of imperfect alignment between the crucible and mold) and
- b) limits the height of part that can be cast to about 300 to 350 mm tall.

1.1.1 250 mm Diameter Cylinders – ACTI-Testworks

The Accelerated Casting Technology Insertion Testworks Program (ACTI-Testworks) program, which ran 2007-2009, was focused on the development of the Direct-Casting process. Much of this project focused on hemispherical shapes and the determination of mechanical properties of Direct Cast U-6Nb. Some limited work was done on cylinders toward the end of the program.

An 8 mm thick cylinder with 239 mm ID, 255 mm OD, and 350 mm tall was attempted by both top-pour and counter-gravity casting. The top-pour cylinder overflowed the funnel above the filter and the did not fully fill the casting cavity. The counter-gravity casting had a funnel and filter-holder at the top of the downsprue. The metal filled the cylinder by dropping down a vertical downsprue entering 6 radial runners and then up the cylinder. The momentum of the molten metal impacted the top of the cylindrical mold in a manner similar to a water hammer. The momentum was sufficient to fracture the bottom of the mold. The molten metal then drained out into the furnace bottom rather than filling the cylinder.

1.1.2 120 mm Diameter Cylinders

Based on the Testworks problems with the 250 mm diameter cylinders, it was next decided to work with a smaller scale cylindrical casting. As discussed in the report Direct Cast U-6Nb – 2017 Progress on Cylindrical Castings [1], the casting cylinder with 120 mm ID and 180 mm tall was investigated.

In this study the segregation of niobium (Nb) in top-filled cylinders was examined as a function of initial mold temperature and casting thickness. Both 8 mm and 16 mm castings were considered. The top-filled cylinders always exhibited significant macrosegregation of Nb. Macrosegregation became more severe as the cylinder thickness and mold temperature was increased. The bottom of the casting was typically about 4% Nb with the top above 6%.

Counter-gravity castings were also made as a function of initial mold temperature for the 8 mm thick castings [1-2]. Depending on the initial mold temperature at pour time there were issues with complete filling of the mold. For those castings that did properly fill, the resulting Nb concentration was uniform from top to bottom.

1.1.3 250 mm Diameter Cylinders – Revisited

Based on the design experience gained with the 120 mm diameter by 180 mm tall small cylinders, work returned to the 250 mm diameter by 350 mm tall small cylinders [1]. The mold designs used in this 2017 work differed from the earlier ACTI Testworks cylinder work in that the filter was relocated from just below the funnel to at the base of the downsprue. In this lower location the filter can act as a flow control, limiting the momentum of the fluid entering the mold cavity. This was intended to help avoid the water hammer like affect and fracture of the mold. This approach was unsuccessful and the two castings attempted did not fill the casting cavity.

To address the shortcomings of this design an integrated mold stack approach, without a funnel, was recommended. On the left side of Fig. 1.1 the furnace with counter-gravity mold stack is shown. For a reasonably tall cylinder, the height limitations of this configuration does not allow the needed separation between the top mold coil (to heat the funnel) from the mold top (which needs to remain cool). Upon careful consideration, it

becomes apparent that there is an inherent redundancy in this design, in that there is the very hot crucible above the hot funnel. Why is a funnel needed at all?

If the down-sprue was extended all the way to the crucible, and the crucible sealed against the down-sprue, the funnel would be unnecessary. Such funnel-less approach is shown on right side of Fig. 1.1. Such a mold design would have the same goals as will be discussed in Section 1.3, but now the crucible would be used to heat the down-sprue and maintain mold pressurization during solidification.

Such a funnel-less approach has several major advantages:

- Creates significant separation between crucible coil and top of mold to avoid coupling between top coil and the top of the mold thereby allowing the top of the mold to remain cool.
- Allows for a taller casting.
- Allows the crucible to be used as part of the feeder system thereby reducing metal usage.
- Allows a longer downsprue for additional pressurization of the casting.

1.2 Multi-Zone Furnace and Furnace Modifications

The multi-zone furnace used for the castings discussed in this report were produced in LANL's K-furnace. This furnace is a three-zone vacuum induction melting (VIM) furnace. The three independently controlled induction coils heat the crucible, the mold top and the mold bottom.

The vacuum chamber is a double-wall steel design with cooling water flowing between the inner and outer walls. The vacuum chamber has three main sections: furnace lid, furnace body (attached to supports on the mezzanine level), and the furnace bottom which rides on a hydraulic ram that lowers it to the main floor. The furnace bottom's hydraulic ram penetrates through the floor with the cylinder bottom and pumps located in the basement. Once lowered the vacuum chamber bottom rests on a set of rails allowing it to be pushed out from under the mezzanine so that the mold stack can be accessed by a crane or forklift.

Normally the bottom pour crucible is supported on a shelf, or crucible baseplate, above the mold. This is shown as the "old" configuration Fig. 1.1. The stopper rod is held in place, and removed at pour time, by a hand turned screw and lever mechanism.

The bottom portion of the furnace can be lowered to allow the mold and induction heating coils to be placed and configured. The coils are stacked in the desired location using firebrick as supports. Multiple layers of mica and graphite felt insulation are placed between the mold and coil (and on the top) to insulate the mold. This allows for a great deal of flexibility but requires more hand labor to setup than a furnace with fixed coils and insulation.

Once the mold and coils are set, the bottom portion of the furnace is lifted into place with a hydraulic ram. The furnace lid is then placed on top with a jib crane and the furnace can be evacuated.

The furnace vacuum is produced by a rotary-vane mechanical vacuum pump. For research type castings, the furnace is typically pumped down overnight to allow for much of absorbed moisture to be extracted. After overnight pump down a base vacuum of 30 millitorr and leak rate of less than 2 millitorr/minute is typical.

The crucible has a 35kW Inductotherm VIP Control 35-96R power supply operating at nominally 9.6 kHz [3]. The crucible coil are either 14.25 inch or 18 inch inner diameter and 12.75 inch tall. The molten metal in the crucible can be observed through a sight port in the furnace lid.

The mold coils share a 50 kW Inductotherm Tri-Switch power supply at nominally 3 kHz. The location of the top and bottom mold coils are shown in Fig. 1.1. For different castings the mold coils may be swapped out for either 11 inch ID, 14.25 inch ID, 18 inch ID, or 22 inch ID coils that are 6.25" tall. For the casting in this report the 14.25 inch coils were used.

To accommodate the recommendations from the prior report on cylinders [1], two major modifications were made to K-furnace.

1. The crucible baseplate and insulation below the crucible were replaced with a plate with a 406 mm (16") ID opening.
2. The crucible coil was replaced with a larger diameter coil with 457 mm (18") ID.

This new configuration allows an integrated mold stack with the crucible resting on top of the mold to be used. This configuration also allows for a larger diameter crucible to be used that better accommodates the approximately 100 kg charge of U-6Nb metal that is needed for these large 250 mm by 450 mm cylinder castings.

For smaller castings, or castings where separate mold and crucible is still desired, a "manhole cover" with insulation can be placed in the larger baseplate hole. This manhole cover has the same 100 mm original opening and supports the crucible. This allows the furnace to be used in either of the configurations shown in Fig. 1.1.

1.3 Goals and Casting Design Approach

The design approach for this work is similar to the approach as discussed in previous work [4], but bears repeating.

1.3.1 Goal

The goal of the Direct Casting process is to produce a sound U-6Nb cast blank for subsequent heat treatment and machining. A sound casting implies that there is

- 1) minimal microporosity,
- 2) no macroporosity,

- 3) nearly uniform Nb content, and
- 4) no other defects that could affect performance.

Minimal microporosity is obtained by having a high thermal gradient during solidification. Macroporosity is avoided by good casting and risering practice. Uniform Nb content can be obtained by either

- (i) quickly solidifying the casting or
- (ii) counter-gravity solidification (solidify from top to bottom of casting).

The mechanical properties of U-6Nb are largely controlled by the alpha-double-prime martensite obtained during heat treatment. As such, mechanical properties are largely independent of the as-cast microstructure. This means to a first order there are no requirements on grain size or as-cast microstructure beyond being a sound casting.

1.3.3 Segregation in U-Nb Castings

Historically U-6Nb castings have exhibited significant inverse segregation of Nb. For a casting that slowly solidifies, it is observed that the bottom of the casting is low in Nb and the top of the casting is high in Nb. This trend is most evident in cylinders conventionally cast that solidify from bottom to top [1].

In Fig. 1.2 the uranium rich side of uranium-niobium phase diagram [5-6] is shown. Also shown is the density of the solid and liquid at the melting point as a function of niobium content. The density of the liquid was experimentally determined by Drotning [7]. The density of the solid (shown as a dotted line), is estimated from the published pure U density [8] and the assumption that the compositional dependence of the solid is the same at the dependence determined by Drotning for the liquid.

It is believed that inverse segregation in U-Nb castings occurs based on the following mechanism. The phase diagram, Fig. 1.2, shows that the first solid to form from an U-6Nb liquid cools has a composition of 10wt%Nb. This first solid (F_s), has a density that is lower than the density of the liquid from which it forms (F_L). The density of the first solid is 15.2 g/cm³, while the density of the liquid is 15.5 g/cm³. This difference of approximately 2% means that the first solid to form will want to float because of simple buoyancy considerations.

For alloys solidifying under typical casting conditions, the solid morphology will form as a dendrite. As shown in Fig. 1.3, the dendrite tip will form just below the liquidus temperature. There will be an initial tip and then this stalk undergoes side branching to make secondary and tertiary dendrite arms. As the temperature drops the volume fraction of solid will increase until just above the solidus temperature (at the dendrite root) there will be only a very small fraction of solid left.

Figure 1.4 compares two common solidification morphologies. In the ingot on left, solidification is by columnar grown and the solid grains grow out from the mold wall forming long columnar grains. Here the heat is conducted away from the solid/liquid interface through the solid and out to the mold. As solidification continues the liquid may

become constitutionally supercooled and the solidification morphology may transition to equiaxed free dendritic growth [9].

In the ingot on the right, solidification is by free dendritic growth wherein dendrites nucleate and grow as isolated particles in the metal. If U-6Nb solidifies by free dendritic growth, then solid can float straight away. If U-6Nb solidifies by columnar growth, then solid can float if dendrite arms or tips breakoff (so called dendrite fragmentation). In either case, solid can find itself in the liquid and the density difference will result in flotation of the Nb rich solid. It is believed that this is the mechanism responsible for the inverse segregation observed in slowly cooled U-6Nb castings.

This pattern of macrosegregation is called *inverse segregation* because the phase diagram indicates that the first solid to form is high in niobium, while it is observed is that the first part of the casting to solidify (the bottom) is low in niobium. Since this pattern of macrosegregation is opposite what the phase diagram would suggest it is termed inverse segregation.

1.3.2 Feeding

As the molten metal freezes and solidifies there is a volume contraction. For uranium this volume contraction is on order of 3%. Ideally feed metal will be supplied from a reservoir of liquid metal resulting in a sound casting. This reservoir is variously called a feeder, riser, hot-top, or lug. If fresh feed metal cannot be supplied (or fed) to those portions of the casting undergoing solidification, then solidification defects may result.

In Fig. 1.5 feeding is illustrated for the assumption of columnar growth. In this illustration, the mold is cool on the left and warm at the feeder on the right. In the presence of a high thermal gradient the metal grows in from the wall and liquid feeds from the hot reservoir at the right. The high thermal gradient results in a short distance that the liquid has to feed through the mushy zone (region of solid and liquid).

In the center case of Fig. 1.5, the case of no thermal gradient, the distance metal has to feed from the feeder on the right to the contracting metal of the very left of the part becomes very long. This long feeding distance, and the very torturous flow path through the dendrite arms once the dendrite tips grow together, makes resistance to fluid flow quite high. Such a situation makes feeding difficult and typically results in microporosity.

In the bottom case in Fig. 1.5, the temperature is not continually increasing from left to right. In this case the solid can pinch off and isolate a region of liquid from the feeder. The region of isolated liquid is often referred to as a *hot spot*.

If liquid metal to feed the solidification shrinkage cannot be supplied, the solidification shrinkage leads to regions of negative hydrostatic pressure which acts on the surrounding solid. The two major shrinkage defects that tend to occur in the casting of U-6Nb from this negative pressure are:

Surface Shrinkage – If the strength of the surrounding solid is low, the surface can be drawn in by plastic deformation. This is called solid feeding and results in *surface shrink* type defects.

Porosity – If the strength of the surrounding solid is high, then a void may nucleate resulting in *porosity* defects.

If the porosity is isolated and on the order of the interdendritic spacing, this porosity is referred to as *microporosity* or *interdendritic porosity*. If the microporosity volume fraction is sufficiently high, then the porosity can become interconnected and is referred to as *spongy porosity*.

To avoid shrinkage defects the mold design and process parameters need to allow for the proper feeding of the solidifying metal to accommodate the solidification shrinkage. Following the work of John Campbell [10], the seven feeding rules are:

1. Do not use a feeder, unless absolutely necessary
2. Feeder must solidify at the same time as, or later than, the casting (heat-transfer criterion of Chvorinov).
3. Feeder must contain sufficient liquid to meet the volume-contraction requirement of the casting (volume criteria).
4. The junction between the casting and feeder should not create a hot spot (junction requirement).
5. There must be a path to allow feed metal to reach those regions that require it (feed path requirement).
6. There must be sufficient pressure differential to cause the feed material to flow to where it is needed (pressure gradient requirement).
7. There must be sufficient pressure at all point in the casting to suppress the formation and growth of porosity (pressure requirement).

Feeding is always much easier if the last liquid solidifies in-mass at a single temperature such as with a pure alloy or eutectic. An alloy like U-6Nb with a large solidification range, makes feeding very difficult.

Because of the thin extended nature of the cylinders that are being cast here, the conventional casting approach of having the feeder supply all of the metal for solidification shrinkage is untenable. Instead shrinkage of metal near the near the first part of the casting to solidify is fed by the adjoining region. In turn this region is fed by the adjoining region further along the casting and so on. The final region to solidify is fed by the hot-top or feeder. This approach relies on having very strong directional solidification. In the case of a cylinder being cast by counter-gravity solidification, this means the top of the cylinder needs to solidify first and solidification needs to sweep in a progressive fashion from the top to the bottom of the casting.

2. Counter-Gravity No-Funnel 250 mm Cylinder – 10 mm Thick Version A

This section will discuss the two castings made with the initial Counter-Gravity No-Funnel 250 Cylinder (CGNF 250 Cylinder) version A mold.

2.1 Casting and Mold Design

The cast blank geometry of interest is shown in Fig. 2.1. It is a hollow cylinder with 235 mm ID, 255 OD, and 450 mm tall.

There is a downsprue from the crucible to the filter. The downsprue was purposely made rather large in diameter (38 mm) for two reasons:

1. Allow for a fast delivery of the metal to the mold.
2. The downsprue must remain liquid during solidification. If it freezes off it will no longer be able to apply pressure to the cylinder and a void will form. The large diameter will be slower to cool and help the downsprue to remain molten.

Table 1 lists the cross-sectional area and modulus of the downsprue, runners, and casting. The casting modulus of the downsprue is nearly twice that of the casting. This will help ensure that the downsprue remains molten till after the cylinder has solidified.

At the bottom of the downsprue there is a porous ceramic filter. Metal enters the filter from the top and exits out the side into 6 horizontal runners. The intent was for the runners to be fully in the filter-holder so that the base has a smooth top. This results in only the filter-holder needing mill work during graphite fabrication. To facilitate removing the filter-holder the runners were given a 15° draft on each side. Figure 2.2 shows the cross-section of the trapezoidal runners used along with the parting line between filter-holder and base.

As shown in Table 1 and Fig. 2.2, the cross-sectional area of the 6 runners is 2745 mm² compared to a cross-sectional area of 1140 mm² for the downsprue. Based on a simple mass balance (flow in equals flow out), the metal flow rate should be 2.4 times slower in the runners than in the bottom of the downsprue.

If the molten metal and mold were individually isothermal with no thermal gradient, which they are not, the casting modulus (volume/surface area) of the cylinder should be less than the modulus of the runners and the downsprue to help with directional solidification. For an element of the mold cavity the *casting modulus* is defined as the volume of the element divided by the mold casting surface area. As shown in Table 1, the downsprue has a modulus of 9.5 mm, the runners a modulus of 5.2 mm, and the casting a modulus of 5.0 mm. Thus, under isothermal conditions the runners would solidify just after the casting and the downsprue would remain molten significantly longer.

By having 6 runners, the combined cross-sectional area of the runners is 2.4 x the area of the downsprue. This will allow the flow rate to be less than in the downsprue. A lower

velocity in the runner should result in less turbulence and splashing as the metal enters the cylindrical casting cavity.

Prior work [1] had shown that a chill was needed on the top of the mold to obtain the desired mold temperatures during mold heat up. Heat transfer is such that this chill is not effective in chilling the casting during solidification; solidification is over too quickly for heat to be transferred through the graphite and across the mold/chill interface. Instead the chill acts as a heat sink during heating so that heat that is conducting up the cylinder and does not build up and result in the top of the mold at an undesirably high temperature at pour time.

To provide structural stability to the mold stack, and avoid having the crucible being solely supported by the downsprue, there is a bubble-alumina spacer between the chill and crucible.

Based on the casting cavity geometry shown in Fig. 2.1, the mold was then designed. The design is based off of the cylinder mold used previously with a funnel [1]. It was modified by attaching the downsprue directly to the crucible.

This mold design also takes advantage of the fact that 2" OD by 1.5" ID graphite tubes are commercially available in 36" lengths. By machining the ends to fit and machining to length, the downsprue of the mold could be made far simpler than by hogging out a hollow tube.

The drawings for the version A mold are provided in Appendix A.

The molds were machined from a solid log of HLM grade graphite [11]. HLM is a medium-grain extruded graphite commonly used for molds and crucibles in the casting of uranium. To prevent chemical reaction between the molten uranium and the graphite mold, those parts of the mold and crucible that come in contact with molten uranium were coated with a high purity yttrium-oxide (yttria) mold coating. The commercial Type Y coating from ZYP was used [12]. This yttria mold coating contains approximately 1/2% cellulose based binder in a water carrier. The mold coating was applied with an automotive style paint sprayer and allowed to dry prior to mold assembly.

The casting was instrumented with 25 or 26 thermocouples and the time temperature history recorded with a computer-based data acquisition system. Sixteen stainless-steel sheathed type-K thermocouples (chromel – alumel) were inserted into holes drilled in the graphite mold (1.6 mm or 1/16" OD). Alumina sheathed type-C thermocouple (W-5%Re – W-26%Re) with a bare-bead tip was routed through holes in the mold wall and into the casting cavity at the equator plus 50 mm. The 3.2 mm (1/8") OD alumina sheaths were then cemented in place using Omegabond 600 high temperature chemical set cement [13] to prevent the thermocouple from being pushed out by the hydrostatic pressure of the molten metal.

To filter out large inclusions and oxides from the molten metal, and to provide flow control at the bottom of the downsprue, a porous ceramic filter is used. The filter is commercial produced out of stabilized zirconia (PSZ) with 30 pores per inch [14]. It has a diameter of 60 mm and is 40 mm tall.

2.2 Casting 19K-801 – Mold Version A with $T_{\text{top}}=900^{\circ}\text{C}$ and $T_{\text{bottom}}=1250^{\circ}\text{C}$

A summary of the castings and conditions along with metal charge is given in Table 2.

2.2.1 Casting Setup

The mold stack is shown as positioned in the furnace in Fig. 2.3 with the corresponding induction coil positions. On the left side of the schematic, the insulation used is indicated. On the right hand side the locations of the thermocouples are shown. Table 4 gives the thermocouple tip location in millimeters, where the origin is the center line of the cylinder at the bottom of mold cavity.

The mold stack was assembled upside down. The mold case was placed upside down and the core inserted in. The filter-holder was then placed into the step joint with core. Figure 2.4 shows a bottom view of the filter-holder during assembly. The white coating on the dark graphite is the yttria mold coating. The cream-colored porous zirconia filter is shown in its' pocket in the filter-holder. Once the base was installed, the case was pinned to the base with 1/4" diameter graphite pins in 6 locations radially around the bottom. The mold was then turned upright and assembly continued.

Because of the shallow 4mm depth of the holes for the thermocouples on the 5 mm thick core, the thermocouples were placed in the holes and then cemented in place with the high temperature chemical set cement. Figure 2.5 shows the thermocouples on the core.

In Fig. 2.6 the mold is shown with the thermocouples installed on the mold and the mold stack placed in the furnace. The stainless-steel sheathed type-K thermocouples are the silver wires while the alumina sheathed type-C thermocouples are the segmented white strands. The split steel chill ring is also installed and the bubble alumina spacer.

As shown in Fig. 2.3, graphite felt radiation shield was placed on the inside of the core to minimize radiative heat transfer (shine) from the downsprue to mold core. Graphite felt and mica radiation shield was placed around the outside of the mold stack to prevent radiative heat loss and protect the induction coils. Figure 2.7 shows the mold stack after the installation of the insulation, crucible, and induction coils.

This stack with the bottom furnace tank was then raised and mated with the center portion of the furnace. Once raised into position, the crucible was charged with the charge material and the stopper rod was placed from above. Figure 2.8 shows the crucible with cut slices of U-6Nb ingot and a minor amount (13%) of recycled cylindrical casting around the edges. For casting 19K-801 the metal charge weight was 105.32 kg. This was a deliberate over charge of approximately 30 kg. Three 25 mm thick graphite lids were

placed on top of the crucible prior to placing the vacuum chamber lid on and pumping the furnace down.

2.2.2 Casting and Cooling Curves

Casting

For casting heat number 19K-801, the desired casting parameters (temperature goals) were:

- heat the metal to 1500°C and hold at temperature by reducing power;
- heat the filter-holder and base to about 1250°C and hold, and
- heat mold top to 900°C and pour.

The casting run parameters are summarized in Table 5.

In Fig. 2.9 the thermal history during heat up and casting of 19K-801 is shown along with the furnace power levels for the three separate coils. The vacuum level is also shown. The horizontal dotted lines are the liquidus (1325°C) and solidus (1255°C) temperatures for reference.

At the start of the casting run, crucible coil power was applied at 35 kW. At fifteen minutes into the casting the bottom coil power was applied at 40 kW. As the crucible and mold bottom approached their intended temperatures, the mold top coil was set to 10 kW. The top coil was turned off 4 minutes prior to pour. The temperature of the melt in the crucible was monitored by a two-color optical pyrometer through a port on the top of the furnace and a sight hole through the crucible lid.

Once the temperatures were at the intended values, the mold bottom coil was turned off and the stopper rod was lifted. The power to the crucible was maintained for 3 minutes after pouring to keep the crucible and downsprue hot. Once the mold bottom was below 1255°C, the stopper rod was lowered and resealed to separate the liquid metal in the sprue and crucible. Although this results in the stopper rod being frozen into the remaining metal in the crucible (thereby losing the stopper rod), it ensures that the metal downsprue could solidify and physically separate from the crucible. If the stopper rod was not replaced after casting, the metal in the crucible would form a solid dumbbell-like shape that would require breaking the mold to remove. Ideally there would be just enough metal to fill the mold cavity and downsprue, but for this early research casting overcharging was done to reduce any chance of underfilling.

The temperature of the various mold components and crucible are plotted as a function of vertical distance just before the stopper rod was removed in Fig. 2.10. The case temperature falls with increasing position. The core temperature is very similar to that of the case, though about 15°C higher. The sprue temperature starts out at the base temperature and increases with height. This data is also listed in Table 5. The background colors of some entries in the Table are meant to help comparison of the goal and actual

temperatures. The goal bottom temperature of 1250°C was matched nicely by both the thermocouple at the bottom of the case (TC8) and the thermocouple in the base (TC9).

Cooling Curves

In Fig. 2.11 through 2.14 the thermal history data is plotted just after pouring.

Figure 2.11 shows the temperature for the thermocouples in the mold cavity plotted out to 30 seconds. This expanded view of early after pour time allows mold filling information to be more clearly observed. The thermocouples in the casting cavity can be seen to spike in temperature as metal hits them and then quickly cool. The initial spike is delayed in time between thermocouples as metal progressively fills the mold cavity. The time of the initial spike provides a measure of mold filling time for that location.

For the thermocouple in the sprue (TC17), as metal pours down upon it and splashes during filling the temperature reading bounces around depending on whether the bead is in contact with metal or not. Once the mold fills to the level of the thermocouple, and thermocouple bead is fully immersed, the temperature becomes relatively constant. The first reaction of the sprue thermocouple is taken at time equal zero.

The thermocouples first respond and are immersed as the metal level rises to the position of the thermocouple. The metal is seen to have cooled during filling and have effectively no super heat; the temperature at the thermocouples are only momentarily above the liquidus (or they never reach the liquidus at all). The top of the casting solidifies in seconds and much of the top is within the mushy zone during filling.

The junction of thermocouple 24, at the $z=12$ mm location, broke during assembly. Once the molten metal immersed the tip, the electrical connection was reestablished and it began to read the correct temperature. Thermocouple 23 failed during heating at a location outside of the mold cavity and did not return useful data.

The goal is to have the metal to solidify progressively from top to bottom. From an examination of Fig. 2.11 is seen that the metal at $z = 270$ mm (TC21) and 370 mm (TC20) solidified prior to the metal at $z = 420$ mm (TC19). Thus, shrinkage defects are expected in the top section of the casting around $z = 420$ mm.

The cavity thermocouple data is replotted on a longer time scale in Fig. 2.12. The bottom of the mold ($z = 0$ to 170 mm) cools very slowly through the liquidus. The bottom portion of the casting solidifies progressively with the bottom of the casting the last portion of the cylinder to solidify. The downsprue (TC17) remains hot and above the liquidus well after the rest of the casting is solid.

The time to immersion, temperature at immersion, time to the liquidus, time to solidus, are tabulated for the thermocouples in the mold cavity in Table 8.

From the cavity thermocouples it is seen that the metal loses most of its superheat during filling. The mold top solidifies in seconds. The bottom half cools slowly suggesting that

the mold has thermally saturated in a radial direction. The mold stack eventually becomes isothermal, but heat transfer along the height of the mold is too slow to significantly impact solidification.

The thermocouples in the mold case are shown Fig. 2.13. Note that the lower section of the cylinder is warmer than the bottom of the cylinder at $z = 12$ mm (TC8) and base (TC9). Thermocouples TC8 and TC9 failed just after pouring; TC3 and TC4 failed after 240 and 360 seconds respectively.

Radial Heat Flow

In several locations in the mold stack there are neighboring thermocouples present in the core, the mold cavity/metal, and in the mold case. In Fig. 2.14 the data from these adjacent locations are replotted as a function of time. In all the locations the introduction of the molten metal creates a temperature spike. The superheat and latent heat of fusion of the metal flows into the core and mold case and then all three begin to cool.

It is interesting to note that at the top of the mold ($z = 470$) that the mold cavity becomes much cooler than the mold after about 45 seconds. The mold core and case temperatures continue to rise suggesting heat is flowing into these relatively cool areas of the mold from below. The metal being cooler suggests that as it cooled it may have contracted away from the case and core and is no longer in strong thermal contact.

In the center of the casting ($z = 170$ to 370 mm) that the core, cavity, and mold all become nearly isothermal after approximately 30 to 60 seconds. This suggests that the core, cavity, and mold remain in thermal contact.

At the bottom of the casting, the metal is much cooler than the case.

2.2.3 Breakout

Casting 19K-801 is shown Fig. 2.15. The as-cast weight, including downsprue, was 77.84 kg. The metal fully filled the mold. The first impression of the outside of the casting is that it looks good.

Figure 2.16 shows the top inner surface of the casting prior to washing off the mold coating. Note the darker areas of surface shrinkage at the top of the casting. This is consistent with the thermocouple data which showed the top of the casting ($z = 420$ mm) to solidify after the middle section of the casting.

Figure 2.17 shows a ring of metal flash of approximately 1 mm thick at the casting bottom. This indicates that the mold case was not properly seated to the base at the step joint. Also visible in Fig. 2.17 are some surface connected porosity at the casting bottom.

2.2.4 Analysis

Following breakout, the casting was vacuum heat treated with a 1000°C for a 4 hour homogenization, followed by cooling to 850°C for 1/2 hour, and then oil quenching.

Casting Cut-Up and Metallography

An approximately 10 mm wide slice was cut vertically from the casting wall using a wire EDM as shown in Fig. 2.18. There are several large shrinkage defects in this slice near the top. Again, this is consistent with the observed thermal data which showed top of the casting ($z = 420$ mm) to solidify after the middle section of the casting.

From one side of this center slice, chips for chemical analysis were taken by drilling at the 10, 105, 205, 305, and 405 mm from the casting top.

The slice was then sectioned into the 10 shorter samples. Half of these shorter sections there then, mounted, polished and metallographically photographed (on the side opposite the chem sample drill holes). Figure 2.19 shows the individual low magnification micrographs as a function of position. In Fig. 2.19 the outer surface is on the top of the images for the images.

Image analysis was performed on these optical micrographs to determine the volume fraction of internal microporosity as a function of position. These results are tabulated in Table 9.

Figure 2.18 shows a montage of these low magnification optical micrographs with their original location in the center-slide along for reference. The quantitative microscopy determined microporosity is also indicated. The top section and bottom section show extensive microporosity.

2.3 Casting 19K-807 – Mold Version. A with $T_{\text{top}}=1000^{\circ}\text{C}$ and $T_{\text{bottom}}=1200^{\circ}\text{C}$

Based on the results of 19K-801, the same version A mold was used to recast as a new casting 19K-807 with a higher initial temperature at the top and lower initial temperature at the bottom. A summary of the casting with initial mold temperatures and metal charge is given in Table 2.

2.3.1 Casting Setup

The mold stack is shown as positioned in the furnace in Fig. 2.20 with the corresponding induction coil positions. On the left side of the schematic, the insulation used is indicated. On the right had side the locations of the thermocouples are shown. Table 4 gives the thermocouple tip location in millimeters, where the origin is the bottom of mold cavity. The set up was nearly the same as the previous casting (19K-801), except for the addition of a redundant thermocouple in the base (TC24).

The other difference between this casting and the last, is that the mold coils were raised an additional 12 mm (1/2"). This was done to try to reduce coupling between the bottom mold coil and the graphite catch pan and thus reduce the unwanted heating of the catch pan. In the end it only reduced catch pan heating marginally, but it may have contributed to the difference observed in the bottom of the case (TC8) and base (TC9 & TC25) temperatures observed at pour time mentioned below.

2.3.2 Casting and Cooling Curves

Casting

For casting heat number 19K-807, the desired casting parameters were:

- heat the metal to 1500°C and hold temperature by reducing power;
- heat the filter-holder and base to about 1200°C and hold, and
- heat mold top to 1000°C and pour.

The casting run parameters are summarized in Table 5. This differs from the previous casting in that it was desired to have the base a bit cooler and the mold top 100°C warmer. The warmer top was to try avoid the premature freezing during filling at the top of the cylinder.

In Fig. 2.21 the thermal history during heat up and casting of 19K-807 is shown along with the furnace power levels for the three separate coils. The vacuum level is also shown. The horizontal dotted lines are the liquidus (1325°C) and solidus (1255°C) temperatures for reference.

At the start of the casting run, crucible coil power was applied at 35 kW. At twenty minutes into the casting the bottom coil power was applied at 40 kW. As shown in Fig. 2.21 there was an initial mix-up as the mold top coil was mistakenly applied for approximately 2 minutes before the mistake was noticed and the correct power settings were restored. As the crucible and mold bottom approached their intended temperatures, the mold top coil was reduced to 10 kW. The top coil was run to pour time. The temperature of the melt in the crucible was monitored by a two-color optical pyrometer through a port on the top of the furnace and a sight hole through the crucible lid.

Once the temperatures were at the intended values, the mold coils were turned off and the stopper rod was lifted. The power to the crucible was maintained for 3 minutes after pouring to keep the crucible and downsprue hot. Once the mold bottom was below 1255°C, the stopper rod was lowered and resealed to separate the liquid metal in the sprue and crucible. Although this results in the stopper rod being frozen into the remaining metal in the crucible (thereby losing the stopper rod), but it ensures that the metal downsprue could solidify and physically separate from the crucible.

The temperature of the various mold components and crucible are plotted as a function of vertical distance just before the stopper rod was removed in Fig. 2.22. The case temperature falls with increasing position. The core temperature is very similar to that of the case, though about 15°C higher. The sprue temperature starts out at the base temperature and increases with height. This data is also listed in Table 5. The goal bottom temperature of 1200°C was not matched as well as desired in that the thermocouple at the bottom of the case (TC8) was 1229°C and the thermocouple in the base (TC9 and T23) was 1182 and 1185°C.

Comparing the temperatures at pour time in the case for this casting to the temperature in the case to the previous casting (Fig. 2.10), shows a noticeable kink in the curve for this casting. The temperatures under the top coil are locally higher in this casting. In 18K-801, the mold top coil power was cut before casting and the case thermal gradient was able to smooth out by conduction eliminating the kink.

Cooling Curves

In Fig. 2.23 through 2.26 the thermal history data is plotted just after pouring.

Figure 2.23 shows the temperature for the thermocouples in the mold cavity plotted out to 30 seconds. The metal is seen to have cooled during filling and have effectively no super heat; the temperature at the thermocouples are only momentarily above the liquidus (or they never reach the liquidus at all). The top of the casting solidifies in seconds and much of the top is within the mushy zone during filling. Thermocouple 24, at the $z=12$ mm location, broke during assembly and did not return any useful data.

For the thermocouple in the sprue (TC17), as metal pours down upon it and splashes during filling the temperature reading bounces around depending on whether the bead is in contact with metal or not. Once the mold fills to the level of the thermocouple, and thermocouple bead is fully immersed, the temperature becomes relatively constant. The first reaction of the sprue thermocouple is taken at time equal zero.

As before, goal is to have the metal to solidify progressively from top to bottom. From an examination of Fig. 2.23 is seen that the metal at between 170 mm (TC22) and 470 mm (TC19) solidified at about the same time, and prior to the metal at $z = 420$ mm (TC19). Thus, we would expect shrinkage defects in the top section of the casting around $z = 420$ mm. We would also expect rather poor feeding throughout the rest of the casting

The cavity thermocouple data is replotted on a longer time scale in Fig. 2.24. The bottom of the mold ($z = 0$ to 170 mm) cools very slowly through the liquidus. The bottom portion of the casting solidifies at nearly the same time. The downsprue (TC17) remains hot and above the liquidus well after the rest of the casting is solid. The bottom this casting solidified in roughly half the time of the previous casting (19K-801).

The time to immersion, temperature at immersion, time to the liquidus, time to solidus, are tabulated for the thermocouples in the mold cavity in Table 8.

From the cavity thermocouples it is seen that the metal loses most of its superheat during filling. The mold top solidifies in seconds. The bottom half cools slowly suggesting that the mold has thermally saturated in a radial direction. The mold stack eventually becomes isothermal, but heat transfer along the height of the mold is too slow to significantly impact solidification.

The thermocouples in the mold case are shown Fig. 2.25. Note that the lower section of the cylinder is warmer than the bottom of the cylinder at $z = 12$ mm (TC8) and base (TC9).

Although TC24 in the mold cavity failed, the thermocouples in the mold indicate that the bottom solidified before the center section of the cylinder.

Radial Heat Flow

In several locations in the mold stack there are neighboring thermocouples present in the core, the mold cavity/metal, and in the mold case. In Fig. 2.26 the data from these adjacent locations are replotted as a function of time. In all the locations the introduction of the molten metal creates a temperature spike. The superheat and latent heat of fusion of the metal flows into the core and mold case and then all three begin to cool.

After about 60 seconds, the temperature of the case and cavity become isothermal in the top two-thirds of the cylinder ($z = 170$ mm). In the bottom section of the casting, $z = 170$ mm and the cavity bottom, the cavity temperature is lower than the case temperature. This suggests that the heat is conducting more quickly up the metal than up the graphite mold; and that there is poor heat transfer between the metal and the case.

2.3.3 Breakout

Casting 19K-807 is shown Fig. 2.27. Photos are taken from all 4 sides. The 0° point is taken as the position of the thermocouples in the casting cavity, TC18-24, which can be seen in the 0° image. The as-cast weight, including downsprue, was 77.24 kg. The metal fully filled the mold. The first impression of the outside of the casting is that it looks good.

Figure 2.28 shows the top inner surface of the casting prior to washing off the mold coating. Note the darker areas of surface shrinkage at the top of the casting. This is consistent with the thermocouple data which showed the top of the casting ($z = 420$ mm) to solidify after the middle section of the casting. The warmer initial temperature at the top of the mold did not improve the lack of directional solidification.

Figure 2.29 shows some surface connected porosity at the approximately 30 to 40 mm above the bottom of the casting. There wasn't any significant flash at the base/case joint at the cylinder bottom.

2.3.4 Analysis

Following breakout, the casting was vacuum heat treated with a 1000°C for a 4 hour homogenization, followed by cooling to 850°C for 1/2 hour, and then oil quenched.

Casting Cut-Up and Metallography

An approximately 10 mm wide slice was cut vertically from the casting wall using a wire EDM as shown in Fig. 2.30. From one side of this center slice chips for chemical analysis were taken by drilling at 10, 105, 205, 305, and 405 mm from the casting top.

The slice was then sectioned into the 11 shorter samples. Half of these shorter sections were then, mounted, polished and metallographically photographed (on the side opposite the chem sample drill holes). Figure 2.31 shows the individual low magnification

micrographs as a function of position. In Fig. 2.31 the outer surface is on the top of the images for the images.

Image analysis was performed on these optical micrographs to determine the volume fraction of internal microporosity as a function of position. These results are tabulated in Table 9.

Figure 2.30 shows a montage of these low magnification optical micrographs with their original location in the center-slide along for reference. The quantitative microscopy determined microporosity is also indicated. The bottom sections showed extensive microporosity. The feeder had lower porosity than the section at $z = 70$ mm, again implying that the bottom froze off prior to complete solidification of the cylinder.

3. Top-Fill 250 mm Cylinder – 10 mm Thick

Previous results have shown top-filled cylinder to be highly segregated. It was desired to cast a top-filled cylinder that was as close to the counter-gravity casting 19K-801 as possible for direct comparison. This section will discuss the top-pour cylinder that was cast to try to match the parameters used to cast the counter-gravity cylinder version A of the previous section.

3.1 Casting and Mold Design

The cast blank geometry of interest is shown in Fig. 3.1. It is the hollow cylinder with 235 mm ID, 255 OD, and 450 mm tall that was used in Section 2. A 16 mm thick hot top is placed at the top of the cylinder to help fee solidification shrinkage.

The same 10 mm mold case thickness and 5 mm core thickness was used as for the counter-gravity casting. To fill the mold in an axisymmetric manner, a conical distributor is placed on top of the core. The distributor has 6 spokes that connect to the mold case and help maintain the core position within the case.

The filter and filter-holder where incorporated into the crucible discharge hole at the crucible bottom. A press fit hold down ring served to hold the filter in the filter pocket in the crucible. This hold down ring also serves as a seat for the stopper rod; thus, in the down position the stopper rod maintains the hold down ring, in addition to the press fit.

The mold drawings are given in Appendix B.

3.2 Casting 19K-829 – Top Fill with $T_{top}=1250^{\circ}\text{C}$ and $T_{bottom}=920^{\circ}\text{C}$

The processing parameters where chosen to mirror counter-gravity cast 19K-801. Casting 19K-801 was poured with the mold top at 920°C and the bottom at 1250°C , so for this top-fill casting the top was 1250°C and the bottom was 920°C .

This is perhaps an unfair comparison in that, as was observed in Section 2, an excessive amount of superheat is lost during mold filling of the counter-gravity castings.

A summary of the casting with initial mold temperatures and metal charge is given in Table 3.

3.2.1 Casting Setup

Casting

The casting was instrumented with a total of 26 thermocouples and the time temperature history recorded with a computer-based data acquisition system. Sixteen stainless-steel sheathed type-K thermocouples (chromel – alumel) were inserted into holes drilled in the graphite mold (1.6 mm or 1/16" OD). Eight alumina sheathed type-C thermocouples (W-5%Re – W-26%Re) with a bare-bead tip were routed through holes in the mold wall and

into the casting cavity. The 3.2 mm (1/8") OD alumina sheathes were then cemented in place using Omegabond 600 high temperature chemical set cement to prevent the thermocouples from being pushed out by the hydrostatic pressure of the molten metal. Two additional type-C thermocouples were in the crucible. Locations of the thermocouples are shown in Fig. 3.2 and their positions are tabulated in Table 6.

As shown in Fig. 3.3, a second type-C thermocouple was added in the mold cavity at the 470 mm level in the hot top. Thermocouples 1 and TC3 through 24 are oriented such that they are at the midpoint between two webs of the distributor. Thermocouple 2 is in a hole drilled through the case and into one of the distributor webs. Thermocouple 25 was rotated 45° with respect to TC18, and is below one of the distributor webs. This can be seen in Figures 3.3 and 3.5. Unfortunately, TC26 did not provide good data return (it's discussed here because it's visible in the assembly figures).

Figure 3.3 shows the view inside the cavity and core during setup of casting 19K-829 just prior to installation of mold base. Note core thermocouples cemented in place on inner face of core and type-C thermocouples passing through the case and into the mold cavity. The bare tips of the type-C junctions are also evident. Figure 3.4 shows the mold with the distributor and splash ring installed.

Although not needed to prevent core floatation during casting, the mold case was pinned to the bottom of the core at 3 places. These pins prevented slippage during assembly and during the process of placing the mold in the furnace.

Figure 3.5 shows the mold stack with thermocouples during setup of the top-pour cylinder casting 19K-829 prior to installation of crucible, coils, and insulation. Figure 3.6 shows the mold stack once the induction coils, crucible, and thermal insulation has been installed. As indicated in Fig. 3.2, there is insulation on the outside of the cylinder. There are also layers of graphite felt under the distributor to help prevent radiative heat transfer down from the distributor. This was intended to keep the distributor as hot as possible to minimize premature heat loss and freezing as metal flows over the distributor and into the mold.

For casting 19K-829, the crucible was charged with 78.38 kg of U-6Nb ingot slices. As shown in Fig. 3.7 the ingot slices were further cut in halves and quarters so they fit in the crucible. Also visible in Fig. 3.7 is the ceramic filter just below the filter hold down ring.

3.3.2 Casting and Cooling Curves

Casting

For casting heat number 19K-829, the desired casting parameters were:

- heat the metal in the crucible to 1500°C and hold temperature by reducing power;
- heat the top of the mold (hot top/distributor) to 1250°C and hold, and
- heat mold bottom to 920°C and pour.

The casting run parameters are summarized in Table 7.

In Fig. 3.8 the thermal history during heat up and casting of 19K-829 is shown along with the furnace power levels for the three separate coils. The vacuum level is also shown. The horizontal dotted lines are the liquidus (1325°C) and solidus (1255°C) temperatures for reference.

At the start of the casting run, crucible coil power was applied at 35 kW. At five minutes into the casting the top coil power was applied at 35 kW. At fifteen minutes into the casting the bottom coil power was applied at 5 kW. The top and bottom mold heating coils were run to pour time. The temperature of the melt in the crucible was monitored by a two-color optical pyrometer through a port on the top of the furnace and a sight hole through the crucible lid.

Once the temperatures were at the intended values, the mold coils were turned off and the stopper rod was lifted. The power to the crucible was maintained for 2 minutes after pouring to keep the distributor hot (through radiation off of the crucible bottom).

The temperature of the various mold components and crucible are plotted as a function of vertical distance just before the stopper rod was removed in Fig. 3.9. The case and core temperature increase with increasing position. The core temperature is very similar to that of the case, though about a bit cooler at top and bottom. This data is also listed in Table 7. The goal temperatures we all very close to the desired temperatures at pouring time.

Cooling Curves

In Fig. 3.10 through 3.13 the thermal history data is plotted just after pouring.

Figure 3.10 shows the temperature for the thermocouples in the mold cavity plotted out to 30 seconds. The thermocouple in the casting cavity can be seen to initially jump up in temperature at pour time, bounce around, and then become relatively constant, after which they quickly cool. The interpretation of this behavior is that during mold filling metal is splashing off of the bare thermocouple junction beads and the temperature reading bounces around depending on whether the bead is in contact with metal or not. Once the mold fills to the level of the thermocouple, and thermocouple bead is fully immersed, the temperature becomes relatively constant. This provides a measure of mold filling time for that location. Because the metal is being poured from the top there is a lot of splashing of metal as it flows off of the distributor and down into the casting cavity.

The thermocouples first respond and are immersed at later times as the metal level rises to the position of the thermocouple. The metal is seen to have cooled during filling. There is little superheat in the metal at the bottom of the mold, but the metal at the top of the mold exhibits a great deal of super heat. The bottom of the casting solidifies in seconds.

The cavity thermocouple data is replotted on a longer time scale in Fig. 3.11. The goal is to have the metal to solidify progressively from bottom to top. From Fig. 3.10 and 3.11 we

can see that this goal was met. The top portions of the cylinder take a significant time to fully solidify. Greater superheat is exhibited by the top of the mold.

The time to immersion, temperature at immersion, time to the liquidus, time to solidus, are tabulated for the thermocouples in the mold cavity in Table 8.

The thermocouples in the mold case are shown Fig. 3.12. The thermocouples show the spike in temperature at pour time and subsequent cooling of the mold. The case cooling is similar to the cavity thermocouples. The distributor exhibits the greatest thermal spike as the hot metal pours over it during filling.

Radial Heat Flow

In several locations in the mold stack there are neighboring thermocouples present in the core, the mold cavity/metal, and in the mold case. In Fig. 3.13 the data from these adjacent locations are replotted as a function of time. In all the locations the introduction of the molten metal creates a temperature spike. The superheat and latent heat of fusion of the metal flows into the core and mold case and then all three begin to cool.

In general, the core heats faster during the initial spike because of its lower thermal mass because it is half the thickness of the case. The cavity tends to be warmer than the case and core. The cavity bottom remains quite cool and solidification is quite quick.

3.2.3 Breakout

The resulting casting (19K-829) is shown Fig. 3.14 from all four sides. The 0° point is taken as the position of the thermocouples in the casting cavity, TC18-24, which can be seen in the 0° image. The metal fully filled the mold and actually overfilled a bit as metal was above the webs of the distributor. The holes left by breaking out the distributor webs can be seen at the top of the casting. The overall impression of the of the casting is that it looks sound.

The as-cast weight was 75.22 kg. The casting yield (e.g. casting weight divided by charge weight) is 95.8% and is typical of the casting yields where 100% ingot is used as the charge material.

3.2.4 Analysis

Following breakout, the casting was vacuum heat treated with a 1000°C for a 4 hour homogenization, followed by cooling to 850°C for 1/2 hour, and then oil quenched.

Casting Cut-Up and Metallography

An approximately 10 mm wide slice was cut vertically from the casting wall using a bandsaw as shown in Fig. 3.15.

From one side of this center slice chips for chemical analysis were taken by drilling eleven samples at the 10, 60, 110, 160, 210, ,260, 310, 360, 410, 440, and 460 mm from the casting bottom. A higher special resolution was chosen for this casting under the

expectation that macrosegregation would be more severe than in the counter-gravity cast cylinders.

The slice was then sectioned into the 12 shorter samples. Half of these shorter sections were then, mounted, polished and metallographically photographed (on the side opposite the chem sample drill holes). Figure 3.16 shows the individual low magnification micrographs as a function of position. In Fig. 3.16 the outer surface is on the top of the images for the images.

Image analysis was performed on these optical micrographs to determine the volume fraction of internal microporosity as a function of position. These results are tabulated in Table 9.

Figure 3.15 shows a montage of these low magnification optical micrographs with their original location in the center-slide along for reference. The quantitative microscopy determined microporosity is quite low in the lower section of the cylinder but then increased as the hot top was approached. The porosity at $z = 405$ mm is as high as the hot-top suggesting that the hot top was not entirely effective for the top of the casting. The large round black features in the bottom two sample locations are holes drilled in the backside of the strip for chemistry samples. During metallographic preparation grinding removed sufficient material to uncover these holes.

4. Counter-Gravity No-Funnel 250 mm Cylinder – 12 mm Thick Version B

This section will discuss the two castings made with the revised Counter-Gravity No-Funnel 250 Cylinder (CGNF 250 Cylinder) version B mold. As discussed below, the major changes from version A are:

1. The casting thickness was increased from 10 to 12 mm and
2. The runners were redesigned and reduced from 6 to 4.

4.1 Casting and Mold Design

The cast blank geometry of interest is shown in Fig. 4.1. It is a hollow cylinder with 231 mm ID, 255 OD, and 450 mm tall. This is the same OD as the version A mold, but with a smaller ID in order to produce a 12 mm thick casting.

4.1.1 Change in Casting Thickness

The increase in cylinder thickness from 10 to 12 mm between the version A and version B mold design was driven by two factors:

1. The desire to give the machinists a bit more machining stock in light of the distortion and out-of-roundness produced during heat treatment quench.
2. The desire to provide more superheat to metal as it flows to fill the top of the casting. The easiest way to accomplish this is increase the volume to surface-area ratio (casting modulus). In turn, the easiest way to do this is to increase the thickness of the cylinder.

4.1.2 Runner Redesign

One significant problem with the runner design of the version A mold was that once the casting cooled down the runners and cylinder shrunk such that the filter-holder was under a great deal of compression and had to be broken. As undesirable as it to have to treat the filter-holder as a disposable item, the high amount of compression on the mold also made it very difficult to break. The 15° draft of the 25 mm height of the runner was insufficient.

To attempt to improve this situation, the runner was redesigned and made hexagonal with the mold parting line half way through the runner. As shown in Fig. 2.2, the top half of the hexagonal runner is in the filter-holder and the bottom half is in the base. By changing to a hexagonal runner, with the parting line at halfway through the hexagonal, the draft angle is increased to 30° and the depth is half of the trapezoidal runner.

In addition, the small 60° angle between the 6 runners in the version A design, meant there was a pie section of filter-holder flanked by two runners and a section of the cylinder compressing the filter-holder. To help reduce this problem it was decided to go to 4 runners. By going to 4 runners this angle was opened up to 90°. Consideration was made

to go to only 3 runners, but the worry was that this might further reduce axisymmetric symmetry of the mold filling.

In Fig. 2.2 the cross-section of downsprue and the gates for mold version A and version B are compared.

From a heat loss standpoint:

1. The total surface area per unit length of 4 hexagonal runners is less than the total surface area per unit length of 4 trapezoidal runners. The hexagonal runners have a surface area per unit length 346 mm² versus 530 mm² for the trapezoidal runners of version A.
2. The cross-sectional area of the runners is reduced. For the same size downsprue this reduction in area will increase the liquid metal flow rate through the runner allowing less time for heat loss in the runners.

The mold drawings for the version B cylinder are given in Appendix C. The addition of slots on the bottom of the base was to allow lifting slings to be placed under the mold stack and to allow a crane to be used to lift the mold stack out of the furnace after casting.

4.2 Casting 19K-844 – Mold Version B with $T_{\text{top}}=1000^{\circ}\text{C}$ and $T_{\text{bottom}}=1250^{\circ}\text{C}$

A summary of the casting with initial mold temperatures and metal charge is given in Table 2.

4.2.1 Casting Setup

The mold stack is shown as positioned in the furnace in Fig. 4.2 with the corresponding induction coil positions. On the left side of the schematic, the layout of the insulation used is indicated. On the right hand side the locations of the thermocouples are shown. Table 4 gives the thermocouple tip locations, where the origin is the bottom of mold cavity.

As before, the mold stack was assembled upside down. The mold case was placed upside down and the core inserted. The filter-holder was then placed into the step joint with the core. Figure 4.3 shows a bottom view of the filter-holder during assembly. The channels that make up the top half of the runners is shown. The round hole between the runners and near the filter is a hole for an orientation pin to maintain angular registry between the base and filter-holder. The white coating on the dark graphite is the yttria mold coating. The porous zirconia filter is shown in its' pocket in the filter-holder.

Figure 4.4 provides a top view of the base showing the channels bottom half of the gating. Once the base was installed, the case was pinned to the base with 1/4" diameter graphite pins in 6 locations radially around the bottom. The mold was then turned upright and assembly continued.

Because of the shallow 4 mm depth of the holes for the thermocouples on the 5 mm thick core, they were inserted in the holes and then cemented in place Omegabond 600 high temperature chemical set cement. Figure 4.5 shows the thermocouples on the core. In

Fig. 4.6 the mold is shown with the thermocouples installed on the mold and the mold stack placed in the furnace. The stainless-steel sheathed type-K thermocouples are the silver wires while the alumina sheathed type-C thermocouples are the segmented white strands. The split steel chill ring is also installed.

As shown in schematically in Fig. 4.2, graphite felt radiation shield was placed on the inside of the core to minimize radiative heat transfer (shine) from the downsprue to mold core. Graphite felt and mica radiation shield was placed around the outside of the mold stack to prevent radiative heat loss and protect the induction coils. The coil positions were lowered from 18K-807 back to the same position as was used for 18K-801.

This stack with the bottom furnace tank was then raised and mated with the center portion of the furnace.

Once raised into position the crucible was charged with the charge material and the stopper rod was placed from above. Figure 4.7 shows the crucible with cut slices of U-6Nb ingot and a recycled cylindrical casting around the edges. For casting 19K-844 the metal charge weight was 97.20 kg. This was a deliberate over charge of approximately 10 kg. Two 25 mm thick graphite lids were placed on top of the crucible prior to placing the vacuum chamber lid on and pumping the furnace down.

4.2.2 Casting and Cooling Curves

Casting

For casting heat number 19K-844, the desired casting parameters were:

- heat the metal to 1500°C and hold temperature by reducing power;
- heat the filter-holder and base to about 1250°C and hold, and
- heat mold top to 1000°C and pour.

The casting run parameters are summarized in Table 5.

In Fig. 4.8 the thermal history during heat up and casting of 19K-844 is shown along with the furnace power levels for the three separate coils. The vacuum level is also shown. The horizontal dotted lines are the liquidus (1325°C) and solidus (1255°C) temperatures for reference.

At the start of the casting run, crucible coil power was applied at 35 kW. At twenty minutes into the casting the bottom coil power was applied at 40 kW. As the crucible and mold bottom approached their intended temperatures, the mold top coil was set to 10 kW. The top and bottom mold coil were run to pour. The temperature of the melt in the crucible was monitored by a two-color optical pyrometer through a port on the top of the furnace and a sight hole through the crucible lid.

Once the temperatures were at the intended values, the mold coils were turned off and the stopper rod was lifted. The power to the crucible was maintained for 3 minutes after pouring to keep the crucible and downsprue hot. Once the mold bottom was below

1255°C, the stopper rod was lowered and reseated to separate the liquid metal in the sprue and crucible.

The temperature of the various mold components and crucible are plotted as a function of vertical distance just before the stopper rod was removed in Fig. 4.9. The case temperature falls with increasing position. The core temperature is very similar to that of the case, though TC10 is significantly warmer (100°C). Overall the heating curve of TC10 is suspect in that it begins heating prior to application of the mold heating. TC10 follows the temperature of the sprue more closely than that of the case. This is not the case with the other counter-gravity castings and may be an issue with the placement of the insulation or a short in the thermocouple.

The sprue temperature starts out at the base temperature and increases with height. This data is also listed in Table 5. The goal bottom temperature of 1250°C was matched nicely by both the thermocouple at the bottom of the case (TC8) and the thermocouples in the base (TC9 and TC25). As with 19K-807, where the top coil was run to pour time, there is a kink in the case thermal gradient.

Cooling Curves

In Fig. 4.10 through 4.13 the thermal history data is plotted just after pouring. As will be discussed in the next section, the bottom of the mold leaked metal out. As such the thermal history data is confounded by the simultaneous partial draining of the metal in the mold cavity and solidification.

Figure 4.10 shows the temperature for the thermocouples in the mold cavity plotted out to 30 seconds. The thermocouple in the casting cavity can be seen to initially jump up in temperature, and then quickly cool.

The thermocouples first respond and are immersed at later times as the metal level rises to the position of the thermocouple. The degree of superheat appears to be better in this 12 mm thick casting than in the previous 10 mm thick cylinder castings. The top of the casting solidifies in seconds and much of the top is within the mushy zone during filling.

The cavity thermocouple data is replotted on a longer time scale in Fig. 4.11. The bottom of the mold ($z = 0$ to 170 mm) cools very slowly through the liquidus.

The goal is to have the metal to solidify progressively from top to bottom. From an examination of Fig. 4.11 is seen that the metal at $z = 70$ mm (TC23) and 17 mm (TC24) solidified prior to the metal in the center of the casting. Thus, we would expect shrinkage defects in the top section of the casting around $z = 420$ mm.

The thermocouples in the mold case are shown Fig. 4.12.

Radial Heat Flow

In several locations in the mold stack there are neighboring thermocouples present in the core, the mold cavity/metal, and in the mold case. In Fig. 4.13 the data from these

adjacent locations are replotted as a function of time. In all the locations the introduction of the molten metal creates a temperature spike. The superheat and latent heat of fusion of the metal flows into the core and mold case and then all three begin to cool.

4.2.3 Breakout

The bottom of the mold stack after casting is shown in Figure 4.14. Approximately 12 kg of metal had leaked out of the bottom joint between case and core. The leaking metal was contained by the felt insulation and mainly flowed into the slots in the bottom of the base.

Casting 19K-844 is shown Fig. 4.15. The as-cast weight, including downsprue, was 79.88 kg. The metal fully filled the mold to the top but on the outer surface there are several linear defects from about 250 mm and down. The bottom of the casting also appears to have a great deal of spongy porosity. Figure 4.16 shows the inner surface of the casting. Note the large area where the metal has drained away leaving a large cavity.

Also apparent in Fig. 4.16 is that the sprue had drained down and was not full. Once the head on the sprue dropped below the level of the molten metal in the cylinder, there was no longer pressure to maintain the liquid level in the cylinder and a macro-void will form in the casting.

Figure 4.15 shows that there is a 1 mm flash at the casting bottom. This indicates that the mold case was not properly seated against the base. This is likely due to the core being slightly too long and mold coating on mating surfaces.

4.2.4 Analysis

Because of the liquid metal leaking out of the mold bottom joint and the partial draining of the casting cavity, it was determined that no useful information could be gained by further analysis of the casting. Metallographic and chemical characterization was not performed.

4.3 Casting 19K-845 – Mold Version B with $T_{\text{top}}=1000^{\circ}\text{C}$ and $T_{\text{bottom}}=1230^{\circ}\text{C}$

Because of the metal leak in casting 19K-844, this casting was repeated as casting 19K-845. A summary of the casting with initial mold temperatures and metal charge is given in Table 2.

4.3.1 Casting Setup

Casting 19K-845 was set up identically to 18K-844 with only minor changes to the thermocouple layout. A total of 26 thermocouples was used as shown in Fig. 4.17.

Because the metal in all of the previous castings stayed molten in the sprue for at least 12 minutes, it was decided that a better use of the limited number of type-C thermocouples was to move it the cylinder proper. As shown in Fig. 4.17, a second type-C thermocouple was added in the mold cavity at the 70 mm and 270 mm levels. Thermocouples 18 through 24 remain at their previous locations at the midpoint between

two gates. Thermocouples 25 and 26 are at the same 70 mm and 270 mm height at TC 21 and TC23, but are rotated 45° such that they are right above the gate. This can be seen in Fig. 4.18.

Figure 4.19 shows the crucible with mostly recycled cylindrical castings (88%) and one quarter slice of ingot. Of the recycled material used, 39% was from a top-poured cylindrical casting; the possible impact of this choice for charge will be discussed in Section 5.4. The metal charge weight was 107.16 kg. This was a deliberate over charge of approximately 15 kg. Two 25 mm thick graphite lids were placed on top of the crucible.

4.3.2 Casting and Cooling Curves

Casting

For casting heat number 19K-845, the desired casting parameters were:

- heat the metal to 1500°C and hold temperature by reducing power;
- heat the filter-holder and base to about 1230°C and hold, and
- heat mold top to 1000°C and pour.

The casting run parameters are summarized in Table 5. This differs from the previous casting in that it was desired to have the base temperature a bit more below the liquidus (1255°C) temperature to avoid metal leakage at the mold bottom. The top of the mold was the same 1000°C.

In Fig. 4.20 the thermal history during heat up and casting of 19K-845 is shown along with the furnace power levels for the three separate coils. The vacuum level is also shown. The horizontal dotted lines are the liquidus (1325°C) and solidus (1255°C) temperatures for reference. In Fig. 4.21 the thermal history of the core and corresponding mold thermocouples is shown during heating.

At the start of the casting run, crucible coil power was applied at 35 kW. At twenty minutes into the casting the bottom coil power was applied at 40 kW. As the crucible and mold bottom approached their intended temperatures, the mold top coil was reduced to 10 kW. The top coil was turned off 6 minutes and 30 seconds before pour time. The temperature of the melt in the crucible was monitored by a two-color optical pyrometer.

Once the temperatures were at the intended values, the mold bottom coil was turned off and the stopper rod was lifted. The power to the crucible was maintained for 3 minutes after pouring to keep the crucible and downsprue hot. Once the mold bottom was below 1255°C, the stopper rod was lowered and resealed to separate the liquid metal in the sprue and crucible.

The temperature of the various mold components and crucible are plotted as a function of vertical distance just before the stopper rod was removed in Fig. 4.21. The case temperature falls with increasing position. The core temperature is very similar to that of the case, though the core is 33°C warmer at the mold top. The sprue temperature starts out at the base temperature and increases with height. This data is also listed in Table 5.

The goal bottom temperature of 1250°C was matched nicely by both the thermocouple at the bottom of the case (TC8) and the thermocouples in the base (TC9).

The same basic run profile as used for both 19K-844 and 19K-845 with the difference that 19K-844 ran the top coil was run to pour time while in 19K-845 was cut 6 minutes before pour time. In 19K-844 (Fig. 4.9) there is a kink in the temperature profile of the case under the top mold coil at pour time. By turning off the top coil before pour the case temperature was able smooth its' self out and, as shown in Fig. 4.22, the case temperature is far more linear with position. This also resulted in the core at the top of the casting ($z = 470$ mm / TC10) being 75°C cooler in 19K-845 than it was for 19K-844 at pour time.

Cooling Curves

In Fig. 4.23 through 4.26 the thermal history data is plotted just after pouring.

Figure 4.23 shows the temperature for the thermocouples in the mold cavity plotted out to 30 seconds. The fill is nicely progressive with the thermocouples in the bottom responding and being immersed in sequential order up to the top. Some superheat is maintained during filling of the lower part of the mold, but by the time the metal reaches above 370 mm the peak temperature is below the liquidus and that filling is in the mushy zone with no superheat.

As before goal is to have the metal to solidify progressively from top to bottom. From an examination of Fig. 4.23 is seen that the metal at between 270 mm (TC22) and the top $z = 420$ mm (TC19) all solidify at about the same time.

The cavity thermocouple data is replotted on a longer time scale in Fig. 4.24. Although thermocouples at $z = 270$ mm (TC21 and TC25) dropped below the solidus temperature at about 8 seconds, they then undergo a thermal recalescence and heat back up into the mushy zone and become isothermal with the other thermocouples down to $z = 70$ (TC23 and 26). The cavity at the bottom solidifies before this middle section of the casting. TC 20 also exhibits a significant recalescence.

The time to immersion, temperature at immersion, time to the liquidus, time to solidus, are tabulated for the thermocouples in the mold cavity in Table 8.

The thermocouples in the mold case are shown Fig. 4.25. The lower section of the cylinder is warmer than the bottom of the cylinder at $z = 12$ mm (TC8) and base (TC9).

Radial Heat Flow

In several locations in the mold stack there are neighboring thermocouples present in the core, the mold cavity/metal, and in the mold case. In Fig. 4.26 the data from these adjacent locations are replotted as a function of time. In all the locations the introduction of the molten metal creates a temperature spike. The superheat and latent heat of fusion of the metal flows into the core and mold case and then all three begin to cool.

4.3.3 Breakout

Casting 19K-845 is shown Fig. 4.27. Photos are taken from all 4 sides. The 0° point is taken as the position of the thermocouples in the casting cavity, TC18-24, which can be seen in the 0° image. On the front side at 0° can be seen the locations where the type-C thermocouples were captured by the solidifying metal.

The as-cast weight, including downsprue, was 91.86 kg. The metal fully filled the mold.

On the mold backside at 180° there is region of significant surface shrink between $z = 130$ and 230 mm. In the photo of the side of the casting (270°) there is a large hot tear at 190 mm.

4.3.4 Analysis

Following breakout, the casting was vacuum heat treated with a 1000°C for a 4 hour homogenization, followed by cooling to 850°C for 1/2 hour, and then oil quenched.

Casting Cut-Up and Metallography

An approximately 10 mm wide slice was cut vertically from the casting wall using a bandsaw as shown in Fig. 4.28. From one side of this center slice chips for chemical analysis were taken by drilling at the 10, 55, 105, 155, 205, 255, 305, 355, 405, and 460 mm from the casting top. The 460 mm sample is in the feeder at the bottom of the casting.

The slice was then sectioned into the 11 shorter samples. Half of these shorter sections there then, mounted, polished and metallographically photographed (on the side opposite the chem sample drill holes). Figure 4.28 shows the individual low magnification micrographs as a function of position. In Fig. 4.29 the outer surface is on the top of the images for the images.

Image analysis was performed on these optical micrographs to determine the volume fraction of internal microporosity as a function of position. These results are tabulated in Table 9.

Figure 4.28 shows a montage of these low magnification optical micrographs with their original location in the center-slide along for reference. The quantitative microscopy determined microporosity is also indicated. The bottom section exhibits some microporosity.

5. Discussion

In this section the results from the various casting are compared. The comparison is to both help determine a best casting approach and set of processing parameters and to try to develop a deeper understanding of the Direct Casting process.

In many respects the casting soundness of the top and bottom of cast cylinder are decoupled with defects in the top primary arising due to filling issues and the defects at the bottom two-thirds of the casting due to premature solidification of the bottom.

5.1 Solidification Time

Solidification time is tabulated in Table 8. For purpose of this report, solidification time is the time for the casting to cool to the solidus of 1255°C. The difference between the pouring temperature and temperature at immersion is an indication of the amount of super heat loss during filling

Figure 5.1 plots solidification time against the distance from cylinder end. For the top-pour cylinder (19K-829), the distance from the casting end is the same as the distance from the cavity bottom. For the counter-gravity cylinders the distance from the casting end is the distance from the cavity top; it's the length of the cylinder with feeder (475 mm) minus the distance from the top (Z).

If solidification was fully directional, then the solidification time would increase with distance. The downturn of the solidification time at the bottom of the counter-gravity castings shows, as we've seen before, that they prematurely froze off at the bottom.

5.2 Microporosity

Internal microporosity from quantitative image analysis of casting cross-sections is tabulated in Table 9. In Fig. 5.2 this data is plotted as volume fraction porosity versus distance from the casting end. For the top-pour cylinder (19K-829), the distance from the casting end is the same as the distance from the cavity bottom. For the counter-gravity cylinders the distance from the casting end is the distance from the cavity top; it's the length of the cylinder with feeder (475 mm) minus the distance from the top (z).

The dotted line at $z = 450$ mm indicates the position that the cylinder transitions to the feeder or hot top.

The first casting, 19K-801, had filling issues and lack of directionality to the solidification. This manifests in the high microporosity the near top of the casting ($z = 100$ mm). The porosity is better in the top of the second casting, 19K-807, but not great in the bottom

The 12 mm thick fourth casting, 19K-845, is quite good in terms of microporosity in the top half of the casting. In the bottom half of the casting the microporosity is high, related to the premature freezing off of the bottom of the cylinder.

For the top-filled cylinder, 19K-829 the bottom half of the casting is quite good. But near the top it is clear that the hot-top was not fully effective in feeding the top of the casting.

5.3 Filling of the Casting Cavity

Time to thermocouple immersion is tabulated in Table 8. For the counter-gravity casting this immersion time is plotted against distance from the casting bottom in Fig. 5.3. This filling time plot give an estimate of the filling rate and filling time. Overall for these approximately 100 kg casting the mold cavity fills in about 7 seconds.

This is a vast improvement over prior crucible with funnel designs where a 20 mm crucible pour hole was used and the fill times were on order of 20 to 30 seconds.

5.4 Chemical Analysis

As noted in the previous sections, chip samples were drilled as a function as position for chemical analysis.

LANL ISP-MS Method

Chips were analyzed for niobium content using inductively coupled plasma – mass spectroscopy (ICP-MS). Dissolution process was done with Aqua Regia preparations. (3:1 HCL:HNO₃). After heating, an additional 1 mL of concentrated HF and 2 mL of aqua regia were added to each sample to ensure that Nb is retained in solution. Digestions were as storage solutions until the day of instrumental analysis. Initial instrumental analysis was performed on an Agilent 7700 ICP-MS. Table 10 summarizes the results.

LANL and Y-12 ICP-MS Method

Chips samples were also allayed at LANL and Y-12 using inductively coupled plasma – optical emission spectroscopy (IPC-OES) [15]. Samples were digested in 8M HNO₃/1M HF/1M HCl solution. For samples where there was particulate in the solution, 1M HF was added until all the solids went into solution. After appropriate dilution, each sample was analyzed by both ICP-OES. These results are also summarized in Table 10.

Chemistry Discussion

Both sets of results are plotted as a function of position from the bottom of the casting in Figures 5.4 through 5.7. The individual data points are plotted with the average value shown as a dotted line.

For counter-gravity castings 19K-801 (Fig. 5.4) and 19K-807 (Fig. 5.5) the chemistry is roughly constant and within the 5.2 and 6.5 weight percent lower and upper limits of the composition given by the DU-6wt% Niobium Alloy specification OO-M-200 [16].

For counter-gravity casting 19K-845 (Fig. 5.6) the chemistry is roughly constant, but many of the values lie below the minimum specification. The overall average is 5.06 wt% Nb. It is not known the exact origin of this lack of Nb. The charge for 19K-845 contained 40%

of a top-pour casting that was recycled into this casting. This top-pour casting was likely was segregated and may be the source of the lack of Nb.

The historic experience with top-pour U-6Nb castings is that result in a part this is heavily macro-segregated top-to-bottom [1-2]. The fact that 19K-829 (Fig. 7) does not show macro-segregation is surprising and not understood. This will be result that will need to be addressed in future castings and development.

6. Conclusions and Design Recommendations

Although there was significant improvement in the castings of this study compared to earlier mold designs which used a funnel, overall these molds fail for the following reasons:

1. Solidify too quickly at top of casting.
2. The temperature of the mold saturates and solidification through the mushy zone takes a very long time.
3. Solidification was not always progressive with directional solidification from top to the feeder.

The top of cylinder solidifies then solidification of the rest of the casting stalls out with no place for the heat to go too. Rev B mold has much better filling than rev A. design, but improvement is still needed.

For future mold design it is recommended that:

- a) To address the leakage of metal at the bottom of the mold – use a press fit joint at the bottom of the casting, the case / base joint. The casting will then have to be removed from the mold from the top, rather than the bottom of the mold.
- b) To address the stagnation and slow solidification of the bottom section of the cylinder – Decrease mold thermal mass in the hot bottom section of the mold and increase mold thermal mass in the cooler middle and top. This can be done by thickening the mold case in the top 2/3rds of the mold.

These mold and process parameters are already incorporated in the next revision (version C) of the CGNF 250 Cylinder mold. Casting with this redesign will be conducted in FY 2020.

7. Acknowledgement

The author would like to acknowledge the financial support of the US Department of Energy through NNSA and NA-123's Component Manufacturing Development (CMD) program.

The author would also like to acknowledge the support of a number of individuals in executing the experiments. Castings support from Seth Imhoff, Gary Sandoval, Ray Sandoval, and Hunter Swenson. Machining support from Jeff Robison and Jeff Vigil. Becky Chamberlin, Mike Rearick and Mike Schappert for chemical analysis. Bob Forsyth and Brianna Alexander for the metallography and quantitative image analysis.

8. References

- [1] R.M. Aikin Jr., "Direct Cast U-6Nb – 2017 Progress on Cylindrical Castings", LA-UR-17-29064 (2017).
- [2] R.M. Aikin Jr., unpublished work on 120 mm counter-gravity cylinders (2018). Work is summarized in "(U) Direct Casting of U-6Nb Components Update", LA-CP 18-00187 (2018).
- [3] Inductotherm Corp., Rancocas, NJ.
- [4] R.M. Aikin Jr., "Process Development and Optimization of a Direct Cast U-6Nb 250 mm Hemispherical Component", LA-UR-18-29233 (2018).
- [5] B.A. Rogers, et al, Trans. Metall. Soc. AIME (1958)
- [6] D. J. Thoma, unpublished data (2004)
- [7] W.D. Drotning, High Temp. High Press., 14, 253-258 (1982)
- [8] Smithells Metals Reference Book, Ed. W.F. Gale and T.C. Totemeier, Elsevier Butterworth Heinemann, Boston, Eighth Ed. 2004.
- [9] W. Kurz and D.J. Fisher, Fundamentals of Solidification, Trans Tech Pub (1984).
- [10] John Campbell, Complete Casting Handbook, 2nd Ed., Elsevier Butterworth-Heinemann, Amsterdam (2015).
- [11] SGL Carbon, LLC., St. Marys, PA USA.
- [12] ZYP Coatings, 120 Valley Court, Oak Ridge, TN USA.
- [13] Omega Engineering Inc., Norwalk, CT.
- [14] ASKChemicals, Alfred Station, NY.
- [15] V.F. Belt, Dissolution and Analysis of Uranium Metal Alloys by Inductively Coupled Plasma Optical Emission Spectroscopy (IPC-OES), Y-12 Procedure Y50-AC-65-6400, revision 0.2 (2019)
- [16] Depleted Uranium – 6 wt% Niobium Alloy, Material Specification OO-M-200 (2000).

TABLES

Table 1
Details of the runner design, casting modulus, and cross-section of downsprue, runners, and casting.

Version A - 10 mm Thick Cylinder

Sprue Dia. (mm) = 38.1				
# of Runners = 6				
base (mm) = 25				
top (mm) = 11.6				
h (mm) = 25				
Cylinder OD (mm) = 255				
Cylinder ID (mm) = 235				
	Cross Section Area (mm)	Area Ratio	Surface Area / Unit Length (mm ²)	Casting Modulus (mm)
Down Sprue	1140.1	1.0	119.7	9.53
Single Runner	457.5	0.74	88.4	5.18
All 6 Runners	2745.0	2.4	530.2	5.18
Cylindrical Casting	7696.9	6.8	1539.4	5.00

Version B - 12 mm Thick Cylinder

Sprue Dia. (mm) = 38.1				
# of Runners = 4				
L (mm) = 14.434				
h (mm) = 12.500				
Cylinder OD (mm) = 259				
Cylinder ID (mm) = 235				
	Cross Section Area (mm)	Area Ratio	Surface Area / Unit Length (mm ²)	Casting Modulus (mm)
Down Sprue	1140.1	1.0	119.7	9.53
Single Runner	541.3	0.72	86.6	6.25
All 4 Runners	2165.1	1.90	346.4	6.25
Cylindrical Casting	9311.7	8.2	1551.9	6.00

Table 2
Summary of 250 mm diameter by 450 mm tall counter- gravity cylinder castings of this study.

Casting ID	Date Cast	Mold Stack Ver.	Cavity Thickness (mm)	Pour Time			Metal				Comments
				Metal (°C)	Mold Top (°C)	Mold Bottom (°C)	Charge Wt. (kg)	Casting Wt. (kg)	Casting Yield (%)	Charge (wt %)	
19K-801	03/04/19	A	10	1512	919	1250	105.32	77.84	n.a.	87% Ingot & 13% Recycled Castings	
19K-807	04/08/19	A	10	1503	1000	1185	88.94	77.24	n.a.	100% Ingot	
19K-844	08/18/19	B	12	1508	1013	1249	97.20	79.88	n.a.	52% Ingot & 48% Recycled Castings	Significant leak at case/base
19K-845	06/27/18	B	12	1508	1000	1226	107.16	91.86	n.a.	11% Ingot & 88% Recycled Castings	

Table 3
The 250 mm diameter by 450 mm tall top-pour cylinder casting of this study.

Casting ID	Date Cast	Mold Stack Ver.	Cavity Thickness (mm)	Pour Time			Metal				Comments
				Metal (°C)	Mold Top (°C)	Mold Bottom (°C)	Charge Wt. (kg)	Casting Wt. (kg)	Casting Yield (%)	Charge Type	
19K-829	05/24/19	J	10	1510	1259	923	78.48	75.22	95.8	100% Ingot	

Table 4
Thermocouple locations for counter-gravity cylinder castings. The origin (z=0) is the bottom of the casting cavity.

19K-801			19K-807			19K-844			19K-845		
Thermocouple	R (mm)	Z (mm)	Thermocouple	R (mm)	Z (mm)	Thermocouple	R (mm)	Z (mm)	Thermocouple	R (mm)	Z (mm)
TC1-Chill	113	518	TC1-Chill	113	518	TC1-Chill	113	518	TC1-Chill	113	518
TC2-Case 470	130	470	TC2-Case 470	130	470	TC2-Case 470	130	470	TC2-Case 470	130	470
TC3-Case 420	130	420	TC3-Case 420	130	420	TC3-Case 420	130	420	TC3-Case 420	130	420
TC4-Mold 370	130	370	TC4-Mold 370	130	370	TC4-Case 370	130	370	TC4-Case 370	130	370
TC5-Case 270	130	270	TC5-Case 270	130	270	TC5-Case 270	130	270	TC5-Case 270	130	270
TC6-Case 170	130	170	TC6-Case 170	130	170	TC6-Case 170	130	170	TC6-Case 170	130	170
TC7-Case 70	130	70	TC7-Case 70	130	70	TC7-Case 70	130	70	TC7-Case 70	130	70
TC8-Case 12	130	12	TC8-Case 12	130	12	TC8-Case 17	130	17	TC8-Case 17	130	17
TC9-Base	130	-5	TC9-Base	130	-5	TC9-Base	130	-5	TC9-Base	130	-5
TC10-Core 470	117	470	TC10-Core 470	117	470	TC10-Core 470	115	470	TC10-Core 470	115	470
TC11-Core 370	117	370	TC11-Core 270	117	270	TC11-Core 270	115	270	TC11-Core 270	115	270
TC12-Core 270	117	270	TC12-Core 70	117	70	TC12-Core 70	115	70	TC12-Core 70	115	70
TC13-Core 170	117	170	TC13-Filter Holder	115	30	TC13-Filter Holder	115	30	TC13-Filter Holder	115	30
TC14-Sprue 505	20	505	TC14-Sprue 505	20	505	TC14-Sprue 505	20	505	TC14-Sprue 505	20	505
TC15-Sprue 170	20	170	TC15-Sprue 120	20	170	TC15-Sprue 95	20	95	TC15-Sprue 95	20	95
TC16-Catchpan			TC16-Catchpan			TC16-Catchpan			TC16-Catchpan		
TC17-Sprue 505	14	505	TC17-Sprue 505	14	505	TC17-Sprue 505	14	505	TC17-Crucible	105	710
TC18-Cavity 470	123	470	TC18-Cavity 470	123	470	TC18-Cavity 470	122	470	TC18-Cavity 470	122	470
TC19-Cavity 420	123	420	TC19-Cavity 420	123	420	TC19-Cavity 420	122	420	TC19-Cavity 420	122	420
TC20-Cavity 370	123	370	TC20-Cavity 370	123	370	TC20-Cavity 370	122	370	TC20-Cavity 370	122	370
TC21-Cavity 270	123	270	TC21-Cavity 270	123	270	TC21-Cavity 270	122	270	TC21-Cavity 270	122	270
TC22-Cavity 170	123	170	TC22-Cavity 170	123	170	TC22-Cavity 170	122	170	TC22-Cavity 170	122	170
TC23-Cavity 70	123	70	TC23-Cavity 70	123	70	TC23-Cavity 70	122	70	TC23-Cavity 70	122	70
TC24-Cavity 12	123	12	TC24-Cavity 12	123	12	TC24-Cavity 17	122	12	TC24-Cavity 17	122	12
TC25-Crucible	65	710	TC25-Base	130	-5	TC25-Base	130	-5	TC25-Cavity 270 Gate	122	270
						TC26-Crucible	105	710	TC26-Cavity 70 Gate	122	70

Table 5
Summary of run parameters and temperature at pour time for counter-gravity cylinder castings.

19K-801		19K-807		19K-844		19K-845	
Mold Design	v. A	Mold Design	v. A	Mold Design	v. B	Mold Design	v. B
Mold Thickness	10 mm	Mold Thickness	10 mm	Mold Thickness	12 mm	Mold Thickness	12 mm
Runners	6 trapazoital	Runners	6 trapazoital	Runners	4 hexagonal	Runners	4 hexagonal
Pour Time Goal Temperature:		Pour Time Goal Temperature:		Pour Time Goal Temperature:		Pour Time Goal Temperature:	
Mold Top	900	Mold Top	1000	Mold Top	1000	Mold Top	1000
Mold Bottom	1250	Mold Bottom	1200	Mold Bottom	1250	Mold Bottom	1230
Metal	1500	Metal	1500	Metal	1500	Metal	1500
Pour time temperatures (°C):		Pour time temperatures (°C):		Pour time temperatures (°C):		Pour time temperatures (°C):	
TC1-Chill	803	TC1-Chill	757	TC1-Chill	887	TC1-Chill	891
TC2-Case 470	919	TC2-Case 470	1001	TC2-Case 470	1013	TC2-Case 470	1000
TC3-Case 420	940	TC3-Case 420	1027	TC3-Case 420	1060	TC3-Case 420	1023
TC4-Mold 370	965	TC4-Mold 370	1052	TC4-Case 370	1103	TC4-Case 370	1049
TC5-Case 270	1030	TC5-Case 270	1072	TC5-Case 270	1134	TC5-Case 270	1103
TC6-Case 170	1101	TC6-Case 170	1113	TC6-Case 170	1165	TC6-Case 170	1154
TC7-Case 70	1195	TC7-Case 70	1193	TC7-Case 70	1236	TC7-Case 70	1207
TC8-Case 12	1251	TC8-Case 12	1229	TC8-Case 17	1264	TC8-Case 17	1229
TC9-Base	1250	TC9-Base	1185	TC9-Base	1249	TC9-Base	1226
TC10-Core 470	936	TC10-Core 470	1017	TC10-Core 470	1116	TC10-Core 470	1042
TC11-Core 370	980	TC11-Core 270	1099	TC11-Core 270	1170	TC11-Core 270	1140
TC12-Core 270	1044	TC12-Core 70	1192	TC12-Core 70	1241	TC12-Core 70	1214
TC13-Core 170	1115	TC13-Filter Holder	1208	TC13-Filter Holder	1251	TC13-Filter Holder	1230
TC14-Sprue 505	1281	TC14-Sprue 505	1227	TC14-Sprue 505	1261	TC14-Sprue 505	1274
TC15-Sprue 170	1221	TC15-Sprue 120	1188	TC15-Sprue 95	1239	TC15-Sprue 95	1240
TC16-Catchpan	513	TC16-Catchpan	452	TC16-Catchpan	626	TC16-Catchpan	593
		TC25-Base	1182	TC25-Base	1255		
TC25-Crucible Btm	1473	TC26-Crucible Btm	-	TC26-Crucible Btm	1442	TC17-Crucible Btm	1444
Pyrometer	1513	Pyrometer	1503	Pyrometer	1508	Pyrometer	1509
Run Time:		Run Time:		Run Time:		Run Time:	
Crucible Soak Time	0:22:01	Crucible Soak Time	0:24:22	Crucible Soak Time	0:27:28	Crucible Soak Time	0:30:21
Time to Pour	1:35:00	Time to Pour	1:27:23	Time to Pour	1:27:58	Time to Pour	1:43:40
Mold top coil off 4:00 prior to pour		Mold top coil power run to pour		Mold top coil power run to pour		Top coil power off 6:30 prior to pour	
Mold bottom coil power reduced at 6:00 prior to pour		Mold bottom coil power reduced 5:15 prior to pour		Mold bottom coil power reduced 4:10 prior to pour		Mold bottom coil power reduced 15:20 prior to pour	

Table 6
Thermocouple locations for top-pour cylinder casting.

19K-825		
Thermocouple	R (mm)	Z (mm)
TC1-Splash Ring	136	606
TC2-Core Web	117	521
TC3-Case 470	136	470
TC4-Case 405	131	405
TC5-Case 305	131	305
TC6-Case 205	131	205
TC7-Case 105	131	105
TC8-Case 55	131	55
TC9-Case 5	131	5
TC10-Core Base	131	-3
TC11-Distributor	2	636
TC12-Core 470	117	470
TC13-Core 405	117	405
TC14-Core 305	117	305
TC15-Core 205	117	205
TC16-Core 105	117	105
TC17-Crucible	90	845
TC18-Cavity 470	123	470
TC19-Cavity 405	123	405
TC20-Cavity 305	123	305
TC21-Cavity 205	123	205
TC22-Cavity 105	123	105
TC23-Cavity 55	123	55
TC24-Cavity 5	123	5
TC25-Below Filter	10	778
TC26-Cavity 470 Gate	123	470

Table 7
Summary of run parameters and temperature at pour time for top-pour cylinder casting.

19K-829	
Mold Thickness	10 mm
Mold Design	Top Fill
Pour Time Goal Temperature:	
Mold Top	1250
Mold Bottom	920
Metal	1510
Pour time temperatures (°C):	
TC1-Splash Ring	1217
TC2-Core Web	1242
TC3-Case 470	1249
TC4-Case 405	1209
TC5-Case 305	1168
TC6-Case 205	1141
TC7-Case 105	1072
TC8-Case 55	1005
TC9-Case 5	923
TC10-Core Base	846
TC11-Distributor	1230
TC12-Core 470	1211
TC13-Core 405	1193
TC14-Core 305	1165
TC15-Core 205	1141
TC16-Core 105	1089
TC17-Crucible	1464
Pyrometer	1512
Run Time:	
Crucible Soak Time	0:30:16
Time to Pour	1:29:24
Mold top coil run to pour	
Mold bottom coil run to pour	

Table 8 Summary of filling and solidification of 250 cylinder castings

Time to Immersion (sec)								
Z (mm)	19K-801	19K-807	Z (mm)	19K-844	19K-845	19K-845 (1)	Z (mm)	19K-829
470	8	7	470	6.6	7.4		470	31.5
420	7	6	420	6.2	6.2		405	26.6
370	6	5	370	5.8	5.4		305	14.6
270	5	4	270	3.1	3.9	3.7	205	10.3
170	3	3	170	2.3	2.7		105	3.3
70	X	2	70	1.4	1.7	1.4	55	2.1
12		X	17	1.0	1.2		5	1.7
Temperature at Immersion (°C)								
Z (mm)	19K-801	19K-807	Z (mm)	19K-844	19K-845	19K-845 (1)	Z (mm)	19K-829
470	1250	1299	470	1324	1300		470	1373
420	1350	1334	420	1358	1317		405	1351
370	1374	1328	370	1364	1341		305	1401
270	1319	1317	270	1387	1377	1367	205	1339
170	1303	1316	170	1392	1352		105	1345
70	X	1332	70	1402	1345	1418	55	1369
12		X	17	1399	1365		5	1330
Time to Liquidus, 1325°C (sec)								
Z (mm)	19K-801	19K-807	Z (mm)	19K-844	19K-845	19K-845 (1)	Z (mm)	19K-829
470	c	c	470	c	c		470	151
420	7	5	420	8.9	c		405	46.7
370	6	5	370	6.6	5.4		305	27.4
270	c	c	270	3.7	4.2	4.3	205	5.0
170	c	c	170	3.1	3.1		105	4.7
70	X	3	70	1.6	2.8	3.1	55	3.9
12		X	17	1.8	2.2		5	1.9
Time to Solidus, 1255°C (sec)								
Z (mm)	19K-801	19K-807	Z (mm)	19K-844	19K-845	19K-845 (1)	Z (mm)	19K-829
470	c	8	470	11	8.4		470	762
420	11	7	420	73	9.6		405	680
370	8	8	370	123	7.1		305	526
270	8	149	270	684	11.5	8.8	205	375
170	317	199	170	742	486		105	122
70	X	158	70	593	572	429	55	17.3
12	385	X	17	473	281		5	3.7

Key:
X – Bad thermocouple
c – Cold metal, temperature never exceed 1325°C or 1255°C
(1) – Thermocouple aligned with gate

Table 9
Internal microporosity from quantitative image analysis of casting cross-sections

Distance from Top (mm)	19K-801	19K-807	19K-845	Distance from Bottom (mm)	19K-829
10	0.06	0.04	0.09	10	0.07
105	1.99	0.18	0.06	110	0.07
205	0.20	0.16	0.07	210	0.06
305	0.41	0.56	0.85	310	0.17
405	8.10	1.03	1.31	410	2.77
465 (feeder)		0.27		460 (feeder)	2.46

Table 10
Chemical analysis results for Nb from 250 mm cast cylinders.

Location (mm)		18K-801 Counter-Gravity 10 mm Thick		
From top	From bottom	LANL ICP-MS	Y-12 ICP-OES	Average
10	465	5.96	6.47	6.22
105	370	6.31	6.24	6.27
205	270	6.16	6.27	6.22
305	170	6.21	6.24	6.22
405	70	6.43	6.39	6.41

Location (mm)		18K-807 Counter-Gravity 10 mm Thick		
From top	From bottom	LANL ICP-MS		
10	465	6.21		
105	370	6.00		
205	270	5.77		
305	170	6.13		
405	70	5.85		
460 (feeder)	15	5.75		

Location (mm)		18K-829 Top-Fill 10 mm Thick		
	From bottom	LANL ICP-MS	Y-12 ICP-OES	Average
	460 (feeder)	6.21	5.77	5.99
	440	5.88	5.73	5.81
	410	5.90	5.83	5.87
	360	5.85	5.76	5.81
	310	5.70	5.78	5.74
	260	6.12	5.80	5.96
	210	5.92	5.87	5.90
	160	5.88	5.48	5.68
	110	5.96	5.55	5.76
	60	6.1	5.59	5.85
	10	5.37	5.74	5.56

Location (mm)		18K-845 Counter-Gravity 12 mm Thick			
From top	From bottom	LANL ICP-MS	LANL ICP-OES	Y-12 ICP-OES	Average
10	465	5.52	5.10	5.14	5.25
55	420	5.29	5.00	5.10	5.13
105	370	4.94	5.01	4.90	4.95
155	320	4.93	4.88	4.91	4.91
205	270	4.98	4.91	4.91	4.93
255	220	5.18	5.01	4.95	5.05
305	170	4.96	5.27	5.05	5.09
355	120	5.29	5.16	4.88	5.11
405	70	5.00	5.27	5.16	5.14
460 (feeder)	15	5.07		4.98	5.03

FIGURES

Fig. 1.1 LANL's three zone K-furnace. Historic configuration is shown on left, and new configuration with modifications to allow an integrated mold/crucible stack is shown on right.

Fig. 1.2 Uranium rich side of uranium-niobium phase diagram (left) and density for solid and liquid at the melting point versus niobium content (right).

Fig. 1.3 Schematic of dendritic growth in a metal alloy. The solid dendrite is growing up into the liquid with a positive thermal gradient.

Fig. 1.4 Comparison of idealized solidification morphologies. In ingot on left solidification is by columnar growth. In ingot on right solidification started by columnar growth and transitioned to equiaxed free dendritic growth.

Fig. 1.5 Idealized columnar solidification in (top) high thermal gradient, (center) low or no thermal gradient, and (bottom) thermal gradient with a hot spot.

TOTAL-
VOLUME = 4878.3 CM3
WEIGHT = 84.64 KG

CASTING -
VOLUME = 3464 CM3
WEIGHT = 60.27 KG

FEEDER FRACTION
= (TOTAL-CASTING)/TOTAL
= 0.290

SECTION A-A

CASTING
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

Fig. 2.1 The 250 cylinder used for casting development work. Casting has 255 mm outer diameter, 450 mm tall, is 10 mm thick, and 6 trapezoidal runners at bottom.

DOWNSPRUE

MOLD VERSION A - 6 trapezoidal runners

MOLD VERSION B - 4 hexagonal runners

Fig. 2.2 Scale cross-section of downsprue and the gates for mold version A and version B. The indicated parting line is between the filter holder and the mold base.

Fig. 2.3 Mold stack for casting 19K-801 with thermocouple, insulation, and induction coil locations. Type C thermocouples exposed in the casting cavity are shown in red; Type K thermocouples imbedded in the graphite mold are shown in blue.

Fig. 2.4 View of bottom of the filter holder and filter during setup of casting 19K-801. Note the 6 runner channels and the ceramic filter at the center.

Fig. 2.5 View looking down to inside the core during setup of casting 19K-801. Note core thermocouples cemented in place on side. Filter holder with filter is visible at bottom.

Fig. 2.6 Mold stack with steel chill and insulating spacer during setup of casting 19K-801 prior to installation of coils and insulation.

Fig. 2.7 Mold stack with insulation and induction heating coils during setup of casting 19K-801.

Fig. 2.8 Crucible with metal charge for 19K-801. Charge is 87% U-6Nb ingot slices and 13% recycled cylindrical castings.

Fig. 2.9 Run chart for the 250 mm x 10 mm thick cylinder 19K-801 showing mold heating and induction power levels used.

Fig. 2.10 Mold temperature as a function of vertical position at pour time ($t=0$) for 19K-801.

Fig. 2.11 Casting 19K-801 cooling curves. Thermocouples in casting cavity during and just after filling.

Fig. 2.12 Casting 19K-801 cooling curves. Thermocouples in casting cavity near pour time.

Fig. 2.13 Casting 19K-801 cooling curves. Thermocouples in mold near pour time.

Fig. 2.14 Casting 19K-801 cooling curves. Thermocouple neighbors as a function of distance from casting cavity bottom.

Fig. 2.15 Casting 19K-801 after breakout and prior to washing off the mold coating. Note flash and rough surface at bottom.

Fig. 2.16 Top inner surface of casting 19K-801 after breakout and prior to washing off the mold coating. Note areas of surface shrinkage.

Fig. 2.17 Bottom outer surface of casting 19K-801. Note flash and spongy porosity at bottom.

Fig. 2.18 Section of 19K-801 along with metallographic sections showing microporosity. The bottom 25 mm of the casting with the gates and feeder was cut off prior to cutting of the slice.

Fig. 2.19 Optical metallography of sections from slice of 19K-801 showing microporosity.

Fig. 2.19 (cont.) Optical metallography of sections from slice of 19K-801 showing microporosity.

Fig. 2.21 Run chart for the 250 mm x 10 mm thick cylinder 19K-807 showing mold heating and induction power levels used.

Fig. 2.22 Mold temperature as a function of vertical position at pour time ($t=0$) for 19K-807.

Fig. 2.23 Casting 19K-807 cooling curves. Thermocouples in casting cavity during and just after filling.

Fig. 2.24 Casting 19K-807 cooling curves. Thermocouples in casting cavity near pour time.

Fig. 2.25 Casting 19K-807 cooling curves. Thermocouples in mold near pour time.

Fig. 2.26 Casting 19K-801 cooling curves. Thermocouple neighbors as a function of distance from casting cavity bottom.

Fig. 2.27 Optical images of 19K-807 from front (0°) and side (90°). Front shows location of type C thermocouples imbedded in the casting cavity.

Fig. 2.27 (cont.) Optical images of 19K-845 from back (180°) and side (270°).

Fig. 2.28 View of top inner surface of casting 19K-807 showing surface shrinkage.

Fig. 2.29 Bottom outer surface of 19K-807 showing surface connected shrinkage.

Fig. 2.30 Section of 19K-807 along with metallographic sections showing microporosity. Slice included the feeder at the bottom.

Fig. 2.31 Optical metallography of sections from slice of 19K-807 showing microporosity.

Fig. 2.31 (cont.) Optical metallography of sections from slice of 19K-807 showing microporosity.

TOTAL -
VOLUME = 4281.4 CM3
WEIGHT = 74.24 KG

CAST PART -
VOLUME = 3463.6 CM3
WEIGHT = 60.09 KG

FEEDER FRACTION
= (TOTAL-CASTING)/TOTAL
= 0.191

PART
TOP POUR 250 MM CYLINDER MOLD
VERSION J

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

Fig. 3.1 Top-pour variant of the 250 cylinder used for casting development work. Casting has 255 mm outer diameter, 450 mm tall, is 10 mm thick, and with a 16 mm thick hot-top.

Fig. 3.3 View inside the cavity and core during setup of casting 19K-829 just prior to installation of mold base. Note core thermocouples cemented in place on inner face of core and thermocouples through the case and into the mold cavity. side.

Fig. 3.4 Top and side view of distributor and splash ring during setup of casting 19K-829. Note the 6 webs that center the distributor to the splash ring and mold case.

Fig. 3.5 Mold stack with thermocouples during setup of casting top-pour cylinder casting 19K-829 prior to installation of crucible, coils, and insulation. Blue tape on top of mold is to exclude contamination during assembly.

Fig. 3.6 Mold stack, coils, and insulation for casting of top-pour cylinder casting 19K-829 prior to installation of top lids.

Fig. 3.7 Crucible with metal charge for 19K-829 prior to seating of the stopper rod. Charge is entirely U-6Nb ingot slices. Filter can be seen below the pour hole.

Fig. 3.8 Run chart for the 250 mm x 10 mm top-pour cylinder 19K-829 showing mold heating and induction power levels used.

Fig. 3.9 Mold temperature as a function of vertical position at pour time ($t=0$) for 19K-829.

Fig. 3.10 Casting 19K-829 cooling curves. Thermocouples in casting cavity during and just after filling.

Fig. 3.11 Casting 19K-829 cooling curves for thermocouples in casting cavity. Cavity location $z = 470$ mm is in the hot top..

Fig. 3.12 Casting 19K-829 cooling curves. Thermocouples in mold near pour time.

Fig. 3.13 Casting 19K-829 cooling curves. Thermocouple neighbors as a function of distance from casting cavity bottom.

Fig. 3.14 Optical images of 19K-829 from front (0°) and side (90°). Front shows location of thermocouples.

Fig. 3.14 (cont.) cont.) Optical images of 19K-829 from back (180°) and side (270°)..

Fig. 3.15 Section of 19K-829 along with metallographic sections showing microporosity. The large round holes in the bottom two metallographic samples are holes drilled on the back side of the strip for chemical analysis chips.

Fig. 3.16 Optical metallography of sections from slice of 19K-829 showing microporosity.

Fig. 3.16 (cont.) Optical metallography of sections from slice of 19K-829 showing microporosity. The large round features in bottom two images are holes drilled for chemistry samples. During metallographic preparation grinding removed sufficient material to uncover these backside holes.

TOTAL-
VOLUME = 5591.1 CM3
WEIGHT = 97.173 KG

CAST CYLINDER -
VOLUME = 4122.4 CM3
WEIGHT = 71.647 KG

FEEDER FRACTION
= (TOTAL-CASTING)/TOTAL
= 0.263

CASTING
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION B

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2019

Fig. 4.1 The version B 250 mm cylinder component used for casting development work. Casting has 255 mm outer diameter, 450 mm tall, is 12 mm thick, and 4 hexagonal runners at bottom.

Fig. 4.2 Mold stack for casting 19K-844 with thermocouple, insulation, and induction coil locations. Type C thermocouples exposed in the casting cavity are shown in red; Type K thermocouples imbedded in the graphite mold are shown in blue.

Fig. 4.3 View of bottom of the filter holder and filter during setup of casting 19K-844. Note the 4 runner channels.

Fig. 4.4 View of top of the base during setup of casting 19K-844. Note the 4 runner channels and pocket for bottom of filter. Hole for alignment pin is also visible.

Fig. 4.5 View looking down to inside the core during setup of casting 19K-844. Note core thermocouples cemented in place on side. Filter holder with filter is visible at bottom.

Fig. 4.6 Mold for casting 19K-844 prior to installation of crucible, coils, and insulation.

Fig. 4.7 Crucible with metal charge for casting 19K-844. Charge is a 52% U-6Nb ingot slices and 48% a recycled cylindrical casting.

Fig. 4.8 Run chart for the 250 mm x 12 mm thick cylinder 19K-844 showing mold heating and induction power levels used.

Fig. 4.9 Mold temperature as a function of vertical position at pour time ($t=0$) for 19K-844.

Fig. 4.10 Casting 19K-844 cooling curves. Thermocouples in casting cavity during and just after filling.

Fig. 4.11 Casting 19K-844 cooling curves. Thermocouples in casting cavity near pour time.

Fig. 4.12 Casting 19K-844 cooling curves. Thermocouples in mold near pour time.

Fig. 4.13 Casting 19K-844 cooling curves. Thermocouple neighbors as a function of distance from casting cavity bottom.

Fig. 4.14 Lower section of mold case and base after casting 19K-844. A significant amount of molten metal seeped through bottom case/base joint prior to solidification.

Fig. 4.15 Optical images of 19K-844 from front (0°) and side (90°). Front shows location of thermocouples.

Fig. 4.15 (cont.) Optical images of 19K-844 from back (180°) and side (270°). Casting has a major surface shrink defect on back side from 130 to 230 mm and a hot tear at approximately

Fig. 4.16 Optical images of inner surface of 19K-844. Showing draining of down sprue and the resulting cavity in the casting.

Fig. 4.17 Mold stack for casting 19K-845 with thermocouple, insulation, and induction coil locations. Type C thermocouples exposed in the casting cavity are shown in red; Type K thermocouples imbedded in the graphite mold are shown in blue.

Fig. 4.18 casting 19K-845 prior to installation of crucible, coils, and insulation. Note that TC25 and TC26 are above the gate, while the other thermocouples are located between gates (a 45° offset).

Fig. 4.19 Crucible with metal charge for 19K-845. Charge is 88% recycled cylindrical castings and a quarter of a U-6Nb ingot slice (12%).

Fig. 4.20 Run chart for the 250 mm x 12 mm thick cylinder 19K-845 showing mold heating and induction power levels used.

Fig. 4.21 Run chart for 19K-845 showing core heating with corresponding mold thermocouples.

Fig. 4.22 Mold temperature as a function of vertical position at pour time ($t=0$) for 19K-845.

Fig. 4.23 Casting 19K-845 cooling curves. Thermocouples in casting cavity during and just after filling.

Fig. 4.24 Casting 19K-845 cooling curves. Thermocouples in casting cavity near pour time.

Fig. 4.25 Casting 19K-845 cooling curves. Thermocouples in mold and chill near pour time.

Fig. 4.26 Casting 19K-845 cooling curves. Thermocouple neighbors as a function of distance from casting cavity bottom.

Fig. 4.27 Optical images of 19K-845 from front (0°) and side (90°). Front shows location of thermocouples. Wrinkle appearing feature at approximately 370 mm from bottom of casting is imprint of graphite machining chatter defects in the mold case.

Fig. 4.27 (cont.) Optical images of 19K-845 from back (180°) and side (270°). Casting has a major surface shrink defect on back side from 130 to 230 mm and a hot tear at approximately 190 mm on the 270° location.

Fig. 4.28 Section of 19K-845 along with metallographic sections showing microporosity. Section on far left shows back side and drill holes for chemistry samples.

Fig. 4.29 Optical metallography of sections from slice of 19K-845 showing microporosity.

Fig. 4.29 (cont.) Optical metallography of sections from slice of 19K-845 showing microporosity. The round features in bottom two images are holes drilled for chemistry samples.

Fig. 5.1 Solidification time (time to solidus) for the 250 mm diameter by 450 mm long cylinders. For the top-pour cylinder 19K-829 the distance from the casting end is the same as the distance from the cavity bottom. For the counter-gravity cylinders the distance from the casting end is the distance from the cavity top (475 mm - Z).

Fig. 5.2 Volume fraction of internal microporosity as a function of position in the casting. Values greater 450 mm are in the feeder. For the top-pour cylinder 19K-829 the distance from the casting end is the same as the distance from the cavity bottom. For the counter-gravity cylinders the distance from the casting end is the distance from the cavity top (475 mm - Z).

Fig. 5.3 Filling time for the counter gravity cylinders. Plot is time of at which thermocouple is immersed in liquid metal versus the thermocouple distance from the bottom. For casting 19K-845 a 2nd order polynomial fit of the data is shown for reference. The slope of this line is the casting filling rate.

Fig. 5.4 Niobium content as a function of position for counter-gravity cylinder 19K-801.

Fig. 5.5 Niobium content as a function of position for counter-gravity cylinder 19K-807.

Fig. 5.6 Niobium content as a function of position for counter-gravity cylinder 19K-845.

Fig. 5.7 Niobium content as a function of position for top-fill cylinder 19K-829.

Appendix A – Counter Gravity No-Funnel 250 mm Cylinder Mold Drawings ver. A (10 mm thick)

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

SECTION A-A

MOLD BASE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

MOLD CASE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

FILTER HOLDER
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

CORE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: PLAIN CARBON STEEL

SPLIT CHILL RING
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: PURIFIED GRAPHITE TUBE
ENDS MACHINED TO DIAMETER ON 2" OD X 1.5" ID TUBE

SPRUE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: CERAMIC INSULATION SUCH AS BUBBLE ALUMINA

SECTION A-A

SPACER
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

14.5 X 1.5 CG CRUCIBLE
14.5 INCH DIAMETER X 10 INCH TALL
1.5 INCH DIAMETER POUR HOLE
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: GRAPHITE

VENTED STOPPER ROD
1-3/4 INCH $\varnothing$ X 17 INCH

ALL DIMENSIONS ARE INCHES
R AIKIN / LANL / SIGMA-1
21-MARCH-2019

Appendix B – Top Pour 250 mm Cylinder Mold Drawings ver. J

CASE
TOP POUR 250 MM CYLINDER MOLD
VERSION J

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

CORE
TOP POUR 250 MM CYLINDER MOLD
VERSION J

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

DETAIL A
SCALE 1.000

SECTION A-A

DISTRIBUTOR
TOP POUR 250 MM CYLINDER MOLD
MOLD STACK - VERSION J

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

SPLASH RING
TOP POUR 250 MM CYLINDER MOLD
VERSION J

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL: FOAM GRAPHITE TBD

SECTION A-A

SPACER
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
11-OCT-2018

MATERIAL:
HLM,6501,OR EQUIVALENT
GRADE OF GRAPHITE

370 Ø CRUCIBLE WITH FILTER
VER A
ALL DIMENSIONS IN MILLIMETERS
19-MARCH-2019
R. AIKIN / SIGMA-1 / LANL
UNCLASSIFIED

MATERIAL:
HLM,6501,OR EQUIVALENT
GRADE OF GRAPHITE

CRUCIBLE INSERT - VER A
370 Ø CRUCIBLE WITH FILTER
ALL DIMENTIONS IN MILLIMETERS
19-MARCH-2019
R. AIKIN / SIGMA-1 / LANL
UNCLASSIFIED

MATERIAL:
HLM,6501,OR EQUIVALENT
GRADE OF GRAPHITE

FILTER HOLD DOWN - VER A
370 Ø CRUCIBLE WITH FILTER
ALL DIMENSIONS IN MILLIMETERS
19-MARCH-2019
R. AIKIN / SIGMA-1 / LANL
UNCLASSIFIED

MATERIAL: GRAPHITE

STOPPER ROD
1-3/4 INCH $\varnothing$ X 15 INCH

ALL DIMENSIONS ARE INCHES
R AIKIN / LANL / SIGMA-1
20-MAY-2019

Appendix C – Counter Gravity No-Funnel 250 mm Cylinder Mold Drawings ver. B (12 mm thick)

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

MOLD BASE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION B

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2019

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

MOLD CASE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION B

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2019

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

FILTER HOLDER
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION B

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2019

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

CORE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION B

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2019

MATERIAL: PURIFIED GRAPHITE TUBE
ENDS MACHINED TO DIAMETER ON 2" OD X 1.5" ID TUBE

SPRUE
CGNF 250 MM CYLINDER MOLD
COUNTER GRAVITY NO FUNNEL
VERSION B

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2018

MATERIAL: HLM GRADE GRAPHITE OR EQUIVALENT

14.5 X 1.5 CG CRUCIBLE
14.5 INCH DIAMETER X 10 INCH TALL
1.5 INCH DIAMETER POUR HOLE
VERSION A

ALL DIMENSIONS ARE MILLIMETERS
R AIKIN / LANL / SIGMA-1
10-JUNE-2019

MATERIAL: GRAPHITE

VENTED STOPPER ROD
1-3/4 INCH $\varnothing$ X 18 INCH

ALL DIMENSIONS ARE INCHES
R AIKIN / LANL / SIGMA-1
21-MARCH-2019